

# Alloys & Tool Steel

## Bar and Plate Products

<b>Toolox® 44 .....</b>	<b>8-2</b>
<b>ETD 150® Analysis &amp; Rounds .....</b>	<b>8-3</b>
<b>AISI 4140/41L40 Products .....</b>	<b>8-4 thru 8-10</b>
<b>AISI 4140/4142 Products .....</b>	<b>8-11 thru 8-14</b>
<b>AISI 4140 As Rolled Plate .....</b>	<b>8-15</b>
<b>AISI 4150 Hot Rolled .....</b>	<b>8-15 thru 8-18</b>
<b>AISI 4340 Hot Rolled .....</b>	<b>8-19 thru 8-21</b>
<b>AISI 6150 HR Annealed .....</b>	<b>8-22 thru 8-25</b>
<b>AISI 8620/86L20 .....</b>	<b>8-26 thru 8-30</b>
<b>AISI 52100 Analysis &amp; Rounds .....</b>	<b>8-31</b>
<b>Alloys Tolerances .....</b>	<b>8-32 thru 8-34</b>
<b>Tool Steel Typical Analysis .....</b>	<b>8-35 thru 8-58</b>
<b>Tool Wrap .....</b>	<b>8-59</b>
<b>Tool Steel Flats &amp; Squares .....</b>	<b>8-59 thru 8-62</b>
<b>Tool Steel Rounds .....</b>	<b>8-63</b>
<b>Tolerances .....</b>	<b>8-64</b>
<b>Machining &amp; Decarb Allowances .....</b>	<b>8-65 thru 8-66</b>



**WARNING:** These products can potentially expose you to chemicals including Nickel, Chromium, Lead, Cobalt, Mercury and Beryllium, which are known to the state of California to cause cancer and/or birth defects or other reproductive harm. For more information, visit [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

# Toolox® 44

## Pre-hardened Steel 45 HRC with ESR Properties

Toolox® 44 is a highly engineered quench & tempered pre-hardened tool and machine steel with measured and guaranteed mechanical properties. Toolox® 44 is delivered ready to use, no heat treating required, saving you valuable production time, reducing risks and lowering overall costs.

Toolox® has ESR properties. The casting process along with the low carbon concept gives a high degree of cleanliness and a homogenous structure.

The high hardness, in combination with excellent toughness, ensures lower tool wear. Toolox® 44 is two to three times tougher than comparable steels of similar hardness.

Additional product features include:

- Easy to machine with good dimensional stability
- High strength and toughness at elevated temperatures
- Excellent for etching, polishing and EDM
- Low residual stresses, no stress relieving required
- Excellent substrate for surface treatments

## Typical Applications

Cold Work Tooling, Machine Components, Wear Components, Guide Rails, Plastic Molds, Rubber Molds, Press Forming, Dies (Forging, Die Cast)

Typical Analysis		Toolox® 44				
Carbon (C)		0.32%				
Silicon (Si)		0.60 - 1.10%				
Manganese (Mn)		0.80%				
Chromium (Cr)		1.35%				
Molybdenum (Mo)		0.80%				
Vanadium		0.14%				
Mechanical Properties		+20°C	+200°C	+300°C	+400°C	+500°C
Hardness (HBW)		450				
Hardness (HRC)		~45				
Yield Strength $R_{p0.2}$ (MPa)		1,300	1,150	1,120	1,060	930
Tensile Strength RM (MPa)		1,450	1,380			
Elongation, A5, (%)		13	10			
Impact toughness, Charpy-V (J)		30	60	80	80	

**Note:** Toolox®44 is not intended for further heat treatment. If Toolox® 44 is heated above 590° after delivery from Alro, no guarantees for the properties of the steel are given.

Thickness (inches)	Weight (lbs./sqft)
5/8	25.524
3/4	30.629
7/8	35.735
1	49.008
1-1/2	69.428

Thickness (inches)	Weight (lbs./sqft)
2	89.848
2-1/2	110.628
3	130.688
4	164.585
5	209.100



# ETD 150®

E.T.D. 150® is produced from AISI medium carbon 4100 series alloy steel. The heats to be used for e.t.d. 150® are controlled to contain nitrogen in quantities normally associated with steel produced by the electric furnace process. Only one additive, such as tellurium, selenium, or sulfur is also added to improve machinability.

Like Fatigue-Proof®, it is another Niagara LaSalle high strength material made by using specially designed dies. It eliminates heat treating and secondary operations such as straightening, finish grinding, cleaning, and inspections. e.t.d.® 150® can be roll threaded, knurled and plated. Suitable for induction hardening, e.t.d.® 150® is also electromagnetically tested using eddy currents and pretested for machinability through Niagara LaSalle's unique testing procedure.

Alloys &  
Tool Steel

Typical Analysis*	ETD 150®
Carbon (C)	0.40 Min
Manganese (Mn)	0.70 / 1.10
Silicon (Si)	0.15 / 0.35
Chromium (Cr)	0.80 / 1.20
Molybdenum (Mo)	0.15 / 0.25

### Mechanical Properties

Tensile Strength.....	**150,000 psi (Min)
Yield Strength (.2% offset).....	130,000psi (Min)
Elongation .....	5% Min
Reduction of Area .....	20% Min
Machinability.....	75% of 1212 (approx)
Rockwell C Hardness .....	**32 (Min)
Brinell Hardness .....	**302 (Min)

*\*ETD 150® contains additives for improving machinability. These may be Tellurium, Selenium, Sulphur (.06 max), or others, separately or in combination.*

*\*\*In the event of disagreement between hardness and tensile strength, the tensile strength shall govern.*

## ETD 150® Rounds

Stock Lengths: 12 foot

Size (inches)	Weight (lbs./foot)	Weight (lbs./12 ft.)
1/2	0.670	8.04
9/16	0.850	10.20
5/8	1.040	12.48
11/16	1.260	15.12
3/4	1.500	18.00
13/16	1.760	21.12
7/8	2.040	24.48
1	2.670	32.04
1-1/16	3.014	36.17
1-1/8	3.379	40.55
1-3/16	3.770	45.24
1-1/4	4.170	50.04

Size (inches)	Weight (lbs./foot)	Weight (lbs./12 ft.)
1-3/8	5.050	60.60
1-1/2	6.010	72.12
1-5/8	7.050	84.60
1-3/4	8.170	98.04
1-7/8	9.390	112.68
2	10.680	128.16
2-1/8	12.06	144.72
2-1/4	13.52	162.24
2-3/8	15.06	180.72
2-1/2	16.69	200.28
2-5/8	18.40	220.80
2-3/4	20.19	242.28
2-7/8	22.07	264.84
3	24.03	288.36
3-1/4	28.21	338.52
3-3/8	30.42	365.04
3-1/2	32.71	392.49

Alro Steel Metals Guide



# AISI 4140/41L40 - Annealed

**HR / CF (Also available in DCF)**

This medium carbon alloy grade is widely used for many general purpose parts requiring high tensile strength and toughness. 4140 contains chromium and molybdenum as alloying elements and may be heat treated over a wide range to give the combined advantages of proper hardness, strength and ductility. In conditions where localized hardness may be required, this steel is readily flame or induction hardened.

Typical Analysis	AISI 4140 / 41L40
Carbon (C)	0.38 / 0.43
Manganese (Mn)	0.75 / 1.00
Silicon (Si)	0.15 / 0.30
Molybdenum (Mo)	0.15 / 0.25
Chromium (Cr)	0.80 / 1.10
Phosphorus (P)	0.035 MAX
Sulphur (S)	0.040 MAX
*Lead	0.15 / 0.35

*\*Applies only to 4140 leaded alloy steel bars.*

# AISI 4140 - Annealed Flats & Squares

**HR (Cut From Plate) (Also available in DCF)**

Size (inches)	Weight (lbs./foot)
<b>3/8 x</b>	
3/8	0.594
1/2	0.765
5/8	0.935
3/4	1.105
1	1.446
1-1/4	1.786
1-1/2	2.126
1-3/4	2.467
2	2.807
2-1/4	3.147
2-1/2	3.488
2-3/4	3.827
3	4.168
3-1/2	4.849
4	5.530
6	8.252
<b>1/2 x</b>	
1/2	1.004
5/8	1.227
3/4	1.451
1	1.897
1-1/4	2.344
1-1/2	2.791
1-3/4	3.237
2	3.684
2-1/4	4.131
2-1/2	4.577
2-3/4	5.024
3	5.471
3-1/2	6.364
4	7.257
4-1/2	8.151
5	9.044
6	10.831
7	12.618
8	14.404
10	17.978
12	21.551
16	28.697
20	35.844
24	42.991
<b>5/8 x</b>	
5/8	1.520
3/4	1.796
1	2.349
1-1/4	2.902
1-1/2	3.455
1-3/4	4.008
2	4.561

Size (inches)	Weight (lbs./foot)
<b>5/8 x</b>	
2-1/4	5.114
2-1/2	5.667
2-3/4	6.220
3	6.773
3-1/2	7.879
4	8.985
4-1/2	10.092
5	11.198
6	13.410
8	17.834
10	22.257
12	26.682
16	35.530
20	44.378
24	53.227
<b>3/4 x</b>	
3/4	2.141
1	2.801
1-1/4	3.460
1-1/2	4.120
1-3/4	4.779
2	5.438
2-1/4	6.098
2-1/2	6.757
2-3/4	7.417
3	8.076
3-1/2	9.395
4	10.713
4-1/2	12.032
5	13.351
6	15.988
8	21.263
10	26.538
12	31.813
16	42.363
20	52.913
24	63.463
<b>1 x</b>	
1	3.704
1-1/8	4.141
1-1/4	4.577
1-1/2	5.449
1-3/4	6.321
2	7.193
2-1/4	8.065
2-1/2	8.937
2-3/4	9.809
3	10.681
3-1/2	12.425

Size (inches)	Weight (lbs./foot)
<b>1 x</b>	
4	14.169
4-1/2	15.914
5	17.658
6	21.146
8	28.123
10	35.099
12	42.076
16	56.028
20	69.981
24	83.934
<b>1-1/4 x</b>	
1-1/4	5.692
1-1/2	6.778
1-3/4	7.862
2	8.947
2-1/4	10.032
2-1/2	11.117
2-3/4	12.201
3	13.286
3-1/2	15.456
4	17.625
4-1/2	19.795
5	21.964
6	26.304
8	34.982
10	43.660
12	52.338
16	69.694
20	87.050
24	104.406
<b>1-1/2 x</b>	
1-1/2	8.106
2	10.702
2-1/4	11.999
2-1/2	13.296
2-3/4	14.594
3	15.891
3-1/2	18.486
4	21.081
4-1/2	23.676
5	26.271
6	31.461
8	41.841
10	52.221
12	62.600
16	83.359
20	104.119
24	124.878

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Note, sizes not listed above can be cut from plate.

Weights above include nominal oversize tolerance. Actual weights may vary.

Continued on next page

# AISI 4140 - Annealed Flats & Squares

**HR (Cut from plate) (Also available in DCF)**

**Alloys &  
Tool Steel**

**Alro Steel Metals Guide**

Size (inches)	Weight (lbs./foot)
<b>1-3/4 x</b>	
1-3/4	10.945
2	12.456
2-1/2	15.476
3	18.497
4	24.537
4-1/2	27.557
5	30.578
6	36.619
8	48.700
10	60.781
12	72.862
16	97.025
20	121.188
24	145.350
<b>2 x</b>	
2	14.210
2-1/4	15.933
2-1/2	17.656
2-3/4	19.379
3	21.102
3-1/2	24.547
4	27.993
4-1/2	31.438
5	34.885
6	41.776
8	55.559
9	62.451
10	69.342
12	83.125
16	110.690
20	138.257
24	165.822
<b>2-1/4 x</b>	
2-1/4	17.900
2-1/2	19.836

Size (inches)	Weight (lbs./foot)
<b>2-1/4 x</b>	
2-3/4	21.771
3	23.707
3-1/2	27.578
4	31.449
4-1/2	35.320
5	39.191
5-1/2	43.063
6	46.934
8	62.418
10	77.903
12	93.387
16	124.357
20	155.326
24	165.823
<b>2-1/2 x</b>	
2-1/2	22.015
2-3/4	24.164
3	26.312
3-1/2	30.609
4	34.905
4-1/2	39.202
5	43.498
5-1/2	47.795
6	52.091
8	69.277
10	86.464
12	103.650
16	138.022
20	172.394
24	206.767
<b>3 x</b>	
3	31.522
3-1/2	36.670
4	41.817
4-1/2	46.964

Size (inches)	Weight (lbs./foot)
<b>3 x</b>	
5	52.112
6	62.406
8	82.996
10	103.585
12	124.174
16	165.353
20	206.532
24	247.711
<b>3-1/2 x</b>	
3-1/2	42.730
4	48.525
4-1/2	54.523
5	60.521
5-1/2	66.723
6	72.518
8	96.510
10	120.502
12	144.495
16	192.480
20	240.465
24	288.451
<b>4 x</b>	
4	55.408
4-1/2	62.257
5	69.106
5-1/2	75.955
6	82.804
8	110.199
10	137.595
12	164.991
16	219.782
20	274.574
24	329.366

*Please refer to pages 8-32 thru 8-34 for alloy tolerances.*

*Sizes not listed above can be cut from plate.*



# AISI 4140 - Annealed Rounds

**HR (Also available in DCF)**

Diameter (inches)	Weight (lbs./foot)
5/8	1.044
3/4	1.500
7/8	2.040
1	2.676
1-1/8	3.384
1-1/4	4.176
1-3/8	5.052
1-1/2	6.012
1-5/8	7.056
1-3/4	8.172
1-7/8	9.384
2	10.680
2-1/8	12.234
2-1/4	13.704
2-3/8	15.258
2-1/2	16.896
2-5/8	18.724
2-3/4	20.533
2-7/8	22.426
3	24.409
3-1/8	26.463
3-1/4	28.872
3-3/8	31.111

Diameter (inches)	Weight (lbs./foot)
3-1/2	33.434
3-5/8	36.070
3-3/4	38.568
4	43.814
4-1/4	49.394
4-1/2	55.309
4-3/4	61.859
5	68.459
5-1/4	75.393
5-1/2	82.661
5-3/4	91.359
6	99.343
6-1/4	107.662
6-1/2	116.315
6-3/4	126.162
7	135.515
7-1/4	145.202
7-1/2	155.224
7-3/4	165.580
8	176.275
8-1/4	187.296
8-1/2	199.737
8-3/4	211.463

Diameter (inches)	Weight (lbs./foot)
9	223.522
9-1/4	235.501
9-1/2	248.207
9-3/4	263.735
10	277.171
10-1/2	305.044
11	334.253
11-1/2	364.796
12	396.675
12-1/2*	429.889
13*	466.624
13-1/2*	502.591
14*	539.893
14-1/2*	578.531
15*	618.503
15-1/2*	659.811
16*	702.454
17*	791.746
18*	886.378
19*	986.351
20*	1091.664
22*	1318.314
24*	1566.326

*\* Sizes above 12" are 16-20' randoms, forged and roughturned.*

*Please refer to pages 8-32 thru 8-34 for alloy tolerances.*

*Stock Lengths: 20 foot*

**Alloys &  
Tool Steel**

## AISI 4140 Rounds - Q&T

Typical Analysis	AISI 4140
Carbon (C)	0.37 / 0.49
Manganese (Mn)	0.65 / 1.10
Silicon (Si)	0.15 / 0.35
Molybdenum (Mo)	0.15 / 0.25
Chromium (Cr)	0.75 / 1.20
Sulphur (S)	.040 MAX
Phosphorus (P)	.035 MAX
<b>Tensile Strength</b>	approx. 110,000 lbs psi
<b>Yield Point</b>	approx. 85,000 lbs psi
<b>Brinell Hardness</b>	269 - 341
<b>Elongation in 2"</b>	16%
<b>Reduction in Area</b>	50%

**Alro Steel Metals Guide**

# AISI 4140 - Rounds

## HR Q&T

Diameter (inches)	Weight (lbs./foot)
3/4	1.500
7/8	2.040
1	2.670
1-1/8	3.379
1-1/4	4.170
1-3/8	5.048
1-1/2	6.010
1-5/8	7.050
1-3/4	8.180
1-7/8	9.387
2	10.680
2-1/8	12.234
2-1/4	13.704
2-3/8	15.258
2-1/2	16.896
2-5/8	18.724
2-3/4	20.533
2-7/8	22.426
3	24.645
3-1/4	28.872
3-1/2	33.434
3-3/4	38.568

Diameter (inches)	Weight (lbs./foot)
4	43.814
4-1/4	49.394
4-1/2	55.309
4-3/4	61.859
5	68.459
5-1/4	75.393
5-1/2	82.661
5-3/4	91.359
6	99.343
6-1/4	107.662
6-1/2	116.315
6-3/4	126.162
7	135.515
7-1/4	145.202
7-1/2	155.224
7-3/4	165.580
8	176.275
8-1/4	187.296
8-1/2	199.737
9	223.522
9-1/2	248.207

Diameter (inches)	Weight (lbs./foot)
10	277.171
10-1/2	305.044
11	334.253
11-1/2	364.796
12	396.675
13	466.624
13-1/2	502.591
14	539.893
14-1/2	578.531
15	618.503
15-1/2	659.811
16	702.454
18	886.378
20	1091.664
22	1318.314
23	1435.275
24	1566.326
26	1826.400
28	2126.440
30	2443.220
32	2776.970

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Stock Lengths: 20 foot randoms, Bars over 10-1/2" diameter are forged.

# AISI 4140 and 41L40\* Annealed Rounds

## Cold Finished

Diameter (inches)	Weight (lbs./foot)
3/16	0.100
1/4	0.170
5/16	0.261
3/8	0.380
7/16	0.510
1/2	0.668
9/16	0.845
5/8	1.043
11/16	1.261
3/4	1.500
13/16	1.763
7/8	2.044
15/16	2.347
1	2.670
1-1/16	3.010

Diameter (inches)	Weight (lbs./foot)
1-1/8	3.379
1-3/16	3.770
1-1/4	4.172
1-5/16	4.600
1-3/8	5.048
1-7/16	5.517
1-1/2	6.008
1-9/16	6.519
1-5/8	7.050
1-3/4	8.177
1-7/8	9.387
1-15/16	10.023
2	10.680
2-1/8	12.057
2-1/4	13.517

Diameter (inches)	Weight (lbs./foot)
2-3/8	15.060
2-1/2	16.688
2-9/16	17.532
2-5/8	18.398
2-3/4	20.192
2-7/8	22.069
3	24.030
3-1/4	28.202
3-1/2	32.708
3-3/4	37.547
4	42.720
4-1/4	48.227
4-1/2	54.068
5	66.750

Refer to pages 8-32 thru 8-34 for alloy tolerances.

Stock Lengths: 12 foot (20 foot available in most sizes).

\*41L40 is a superior free machining direct hardening alloy (Lead of .15/.35).





# AISI 4140/4142 Q&T Rounds

## Cold Finish T&P

4140/4142 CF Q&T SR is a general purpose alloy used where substantial strength, toughness and hardness are required. Through tempering, quenching and the cold-finishing process, the end result is improved strength and ductility, improved toughness, better fatigue resistance and superior surface condition.

4140 CF Q&T SR Rounds are also calcium-treated for improved machinability and fully stress relieved after drawing so that distortion during machining is held to a minimum.

# AISI 4140 Quench & Tempered Rounds

## Cold Finish T&P

Diameter (inches)	Length (feet)	Weight (lbs./foot)
3/8	12	.375
1/2	12	.667
5/8	12	1.042
3/4	12	1.501
7/8	20	2.044
1	20	2.670
1-1/8	20	3.379
1-3/16	20	3.765
1-1/4	20	4.171
1-3/8	20	5.047
1-7/16	20	5.510
1-1/2	20	6.007
1-5/8	20	7.050
1-3/4	20	8.176
1-7/8	20	9.387
1-15/16	20	10.020
2	20	10.680

Diameter (inches)	Length (feet)	Weight (lbs./foot)
2-3/16	20	12.776
2-1/4	20	13.516
2-7/16	20	15.863
2-1/2	20	16.687
2-11/16	20	19.277
2-3/4	20	20.191
2-15/16	20	23.031
3	20	24.030
3-1/4	20	28.202
3-7/16	20	31.541
3-1/2	20	32.707
3-15/16	20	41.384
4	20	42.720
4-7/16	20	52.564
4-1/2	20	54.080
5	20	66.750
6	20	96.120

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Stock Lengths: 12 foot randoms.

# AISI 4140 Annealed Squares

## Cold Finish

Size (inches)	Weight (lbs./foot)
3/8	0.478
1/2	0.850
5/8	1.328
3/4	1.913
7/8	2.603

Size (inches)	Weight (lbs./foot)
1	3.400
1-1/8	4.303
1-1/4	5.313
1-1/2	7.650

Size (inches)	Weight (lbs./foot)
1-3/4	10.413
2	13.600
2-1/2	21.250
3	30.600

# AISI 4140 Annealed Hexagons

## Cold Finish

Size (inches)	Weight (lbs./foot)
3/8	0.413
7/16	0.563
1/2	0.735
9/16	0.930
5/8	1.148
11/16	1.300
3/4	1.654
13/16	1.953
7/8	2.251

Size (inches)	Weight (lbs./foot)
15/16	2.584
1	2.940
1-1/16	3.324
1-1/8	3.721
1-1/4	4.594
1-3/8	5.558
1-7/16	6.085
1-1/2	6.625

Size (inches)	Weight (lbs./foot)
1-5/8	7.763
1-3/4	9.004
1-7/8	10.350
2	11.780
2-1/4	14.910
2-1/2	18.400
2-3/4	22.220
3	26.500

Please refer to pages 8-32 thru 8-33 for alloy tolerances.

Stock Lengths: 12 foot randoms

# AISI 4140 Annealed Flats

## Cold Finish

Size (inches)	Weight (lbs./foot)
<b>1/4 x</b>	
1-1/2	1.28
2	1.70
3	2.55
<b>3/8 x</b>	
1	1.28
1-1/4	1.59
1-1/2	1.91
2	2.55
3	3.83
3-1/2	4.46
4	5.10
<b>1/2 x</b>	
1	1.70
1-1/2	2.55
2	3.40
2-1/2	4.25
3	5.10
4	6.80
4-1/2	7.65
5	8.50
6	10.20
<b>5/8 x</b>	
1	2.13
2	4.25
2-1/2	5.31
3	6.77
4	8.50
5	10.63
6	12.75

Size (inches)	Weight (lbs./foot)
<b>3/4 x</b>	
1	2.55
1-1/4	3.19
1-1/2	3.83
2	5.10
2-1/2	6.38
3	7.65
4	10.20
5	12.75
6	15.30
<b>1 x</b>	
1-1/4	4.25
1-1/2	5.10
1-3/4	5.95
2	6.80
2-1/2	8.50
3	10.20
3-1/2	11.90
4	13.60
5	17.00
6	20.40
7	23.80
8	27.20
<b>1-1/4 x</b>	
1-1/2	6.38
2	8.50
2-1/4	9.56
3	12.75
3-1/2	14.88
4	17.00
4-1/2	19.13

Size (inches)	Weight (lbs./foot)
<b>1-1/4 x</b>	
5	21.25
6	25.50
<b>1-1/2 x</b>	
2	10.20
2-1/2	12.75
3	15.30
3-1/2	17.84
4	20.40
5	25.50
6	30.60
<b>2 x</b>	
2-1/2	17.00
3	20.40
3-1/2	23.80
4	27.20
5	34.00
6	40.80
<b>2-1/2 x</b>	
4	34.00
<b>3 x</b>	
4	40.80
5	51.00

Please refer to pages 8-32 thru 8-34 for alloy tolerances.



# AISI 4140/4142 (MOD) DCF

## Medium Carbon Alloy, Pre-Hardened (Cut From Plate)

Also available in HR

4140/4142 is a fine pre-hardened alloy steel, ready for use and is machinable in its hardened state 260/321 Brinell for thickness under 3" and 241/321 Brinell for 3" and over.

### Typical Applications

Strippers, Holder Blocks, Mold Bases, Ejectors, Back Up and Support Tooling, Fixtures, Jigs, Molds, Cams, and many more applications where time and money are important considerations.

Typical Analysis	AISI 4140/4142 (MOD)
Carbon (C)	0.36 / 0.46
Manganese (Mn)	0.70 / 1.70
Silicon (Si)	0.15 / 0.45
Molybdenum (Mo)	0.15 / 0.35
Chromium (Cr)	0.75 / 1.20
Phosphorus (P)	0.035 max.
Sulphur (S)	0.040 max.
Nickel (Ni)	0.50 max.
<b>Tempering</b>	
Tempering temperature	
Approx. tempered hardness, Rockwell C	26-34
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated</b>	
<b>Temperature</b>	Low
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	Medium
<b>Grindability</b>	High

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

# AISI 4140/4142 (MOD) - Flats & Squares

**Pre-Hardened DCF, HR Pre-Hardened, Annealed DCF and HR Annealed (Cut from Plate)**

**Alloys &  
Tool Steel**

**Alro Steel Metals Guide**

Size (inches)	Weight (lbs./foot)
<b>1/4 x</b>	
1/2	0.540
5/8	0.657
3/4	0.774
1	1.008
1-1/8	1.125
1-1/4	1.242
1-1/2	1.476
1-3/4	1.710
2	1.944
2-1/4	2.178
2-1/2	2.412
2-3/4	2.646
3	2.880
3-1/2	3.348
3-3/4	3.582
4	3.816
4-1/2	4.284
5	4.751
6	5.687
7	6.623
8	7.559
9	8.495
10	9.431
12	13.533
16	17.998
20	22.463
24	26.928
32	35.858
<b>3/8 x</b>	
3/8	0.615
1/2	0.785
5/8	0.956
3/4	1.126
1	1.466
1-1/4	1.806
1-1/2	2.147
1-3/4	2.487
2	2.827
2-1/4	3.168
2-1/2	3.508
2-3/4	3.848
3	4.189
3-1/2	4.869
4	5.550
6	8.272
7	9.634
8	10.995
10	13.718

Size (inches)	Weight (lbs./foot)
<b>3/8 x</b>	
12	18.691
16	24.858
20	31.024
24	37.191
32	49.524
<b>1/2 x</b>	
1/2	1.031
5/8	1.254
3/4	1.478
1	1.924
1-1/4	2.371
1-1/2	2.818
1-3/4	3.264
2	3.711
2-1/4	4.158
2-1/2	4.604
2-3/4	5.051
3	5.498
3-1/2	6.391
4	7.284
5	9.071
6	10.858
6-1/2	11.751
7	12.644
8	14.431
9	16.218
10	18.004
12	23.849
14	27.783
16	31.717
18	35.651
20	39.585
24	47.453
32	63.190
<b>5/8 x</b>	
5/8	1.553
3/4	1.829
1	2.382
1-1/4	2.935
1-1/2	3.488
1-3/4	4.041
2	4.594
2-1/4	5.148
2-1/2	5.701
2-3/4	6.254
3	6.807
3-1/2	7.913
4	9.019

Size (inches)	Weight (lbs./foot)
<b>5/8 x</b>	
4-1/2	10.125
5	11.231
6	13.443
8	17.867
10	22.291
12	29.006
16	38.576
20	48.146
24	57.715
32	76.855
<b>3/4x</b>	
3/4	2.181
1	2.841
1-1/4	3.500
1-1/2	4.159
1-3/4	4.819
2	5.478
2-1/4	6.137
2-1/2	6.797
2-3/4	7.456
3	8.116
3-1/2	9.434
4	10.753
5	13.390
6	16.028
8	21.303
10	26.578
12	34.164
16	45.435
20	56.706
24	67.978
32	90.521
<b>7/8x</b>	
7/8	2.916
1	3.299
1-1/4	4.064
1-1/2	4.830
1-3/4	5.596
2	6.362
2-1/4	7.127
2-1/2	7.893
2-3/4	8.659
3	9.424
3-1/2	10.956
4	12.487
4-1/2	14.019
5	15.550

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Note, sizes not listed above can be cut from plate.

Continued on next page



# AISI 4140/4142 (MOD) - Flats & Squares

**Pre-Hardened DCF, HR Pre-Hardened, Annealed DCF and HR Annealed (Cut from Plate)**

Size (inches)	Weight (lbs./foot)
<b>7/8 x</b>	
6	18.613
8	24.739
10	30.865
12	39.321
16	52.294
20	65.267
24	78.240
32	104.186
<b>1 x</b>	
1	3.757
1-1/4	4.629
1-1/2	5.501
1-3/4	6.373
2	7.245
2-1/4	8.117
2-1/2	8.989
2-3/4	9.861
3	10.733
3-1/2	12.478
4	14.222
4-1/2	15.966
5	17.710
6	21.198
7	24.687
8	28.175
9	31.663
10	35.151
12	44.479
16	59.153
20	73.828
24	88.503
32	117.852
<b>1-1/8 x</b>	
1-1/4	5.193
1-1/2	6.172
2	8.129
2-1/2	10.086
3	12.042
3-1/2	13.999
4	15.956
5	19.870
6	23.783
8	31.611
10	39.438
<b>1-1/8 x 12</b>	49.636
16	66.012
20	82.389
24	98.765
32	131.517

Size (inches)	Weight (lbs./foot)
<b>1-1/4 x</b>	
1-1/4	5.758
1-1/2	6.843
1-3/4	7.927
2	9.012
2-1/4	10.097
2-1/2	11.182
2-3/4	12.267
3	13.351
3-1/2	15.521
4	17.690
4-1/2	19.860
5	22.030
6	26.369
8	35.047
10	43.725
12	54.794
16	72.872
20	90.949
24	109.027
32	145.183
<b>1-3/8 x 1-3/8</b>	6.918
1-1/2	7.514
1-3/4	8.705
2	9.896
2-1/4	11.087
2-1/2	12.278
2-3/4	13.469
3	14.660
3-1/2	17.043
4	19.425
5	24.189
6	28.954
8	38.483
10	48.012
12	59.951
16	79.731
20	99.510
24	119.290
32	158.848
<b>1-1/2 x 1-1/2</b>	8.184
1-3/4	9.482
2	10.779
2-1/4	12.077
2-1/2	13.374
2-3/4	14.672
3	15.969
3-1/2	18.564
4	21.159

Size (inches)	Weight (lbs./foot)
<b>1-1/2 x</b>	
4-1/2	23.754
5	26.349
6	31.539
8	41.919
10	52.298
12	65.109
16	86.590
20	108.071
24	129.552
32	172.514
<b>1-3/4 x</b>	
1-3/4	11.036
2	12.546
3	18.587
3-1/2	21.608
4	24.628
4-1/2	27.648
5	30.669
6	36.709
8	48.791
10	60.872
12	75.424
16	100.308
20	125.192
24	150.077
32	199.845
<b>2 x</b>	
2	14.314
2-1/4	16.036
2-1/2	17.759
2-3/4	19.482
3	21.205
3-1/2	24.651
4	28.097
4-1/2	31.542
5	34.988
6	41.880
8	55.662
10	69.445
12	85.739
16	114.027
20	142.314
24	170.601
32	227.176

Please refer to pages 8-32 thru 8-34 for alloy tolerances.  
Note, sizes not listed above can be cut from plate.

Continued on next page

# AISI 4140/4142 (MOD) - Flats & Squares

**Pre-Hardened DCF, HR Pre-Hardened, Annealed DCF and HR Annealed (Cut from Plate)**

**Alloys &  
Tool Steel**

**Alro Steel Metals Guide**

Size (inches)	Weight (lbs./foot)
<b>2-1/4 x</b> 2-1/4	18.016
2-1/2	19.952
3	23.823
3-1/2	27.694
4	31.565
5	39.308
6	47.050
8	62.534
10	78.019
12	96.054
16	127.745
20	159.435
24	191.126
32	254.507
<b>2-1/2 x</b> 2-1/2	22.144
2-3/4	24.293
3	26.441
3.5	30.737
4	35.034
5	43.627
6	52.220
8	69.406
10	86.592
12	106.369
16	141.463
20	176.557
24	211.651
32	281.838
<b>2-3/4 x</b> 2-3/4	26.698
3	29.059
4	38.503
5	47.947
6	57.390
8	76.278
10	95.166
12	116.684
16	155.181
20	193.678
24	232.175
32	309.169

Size (inches)	Weight (lbs./foot)
<b>3 x</b> 3	31.677
3-1/2	36.824
4	41.971
5	52.266
6	62.561
8	83.150
10	103.739
12	127.000
16	168.900
20	210.800
24	252.700
32	336.500
<b>3-1/2 x</b> 3-1/2	42.911
4	48.909
5	60.905
6	72.901
8	96.894
10	120.887
12	147.630
16	196.336
20	245.043
24	293.749
32	391.163
<b>4 x</b> 4	55.846
5	69.544
6	83.242
8	110.638
10	138.034
12	168.260
16	223.773
20	279.286
24	334.799
32	445.825
<b>4-1/2 x</b> 4-1/2	70.745
5	78.445
6	93.844
8	124.643
10	155.442
12	186.241
16	247.839
20	309.437
24	371.035
32	494.231

Size (inches)	Weight (lbs./foot)
<b>5 x</b> 5	88.550
6	105.832
8	140.394
10	174.957
12	209.520
16	278.646
20	347.772
24	416.898
32	555.149
<b>5-1/2 x</b> 5-1/2	106.761
<b>6 x</b> 6	126.673
8	168.042
10	209.411
12	250.781
16	333.519
24	498.996
32	664.474
<b>7 x</b> 7	171.602
8	195.690
10	243.865
12	292.041
16	388.392
20	484.744
24	581.095
32	773.798
<b>8 x</b> 8	223.337
10	278.319
12	333.301
16	443.266
20	553.230
24	663.194
32	883.122

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Note, sizes not listed above can be cut from plate.



# AISI 4140 - As Rolled Plate

Also available in Annealed & Pre-Hardened

4140 Hot Rolled - As Rolled is available to be saw cut or flame cut to custom sizes.

Thickness (inches)	Weight (lbs./sqft)	Thickness (inches)	Weight (lbs./sqft)	Thickness (inches)	Weight (lbs./sqft)
1/2	20.42	2-3/4	112.30	6	245.04
5/8	25.53	3	122.50	6-1/4	255.25
3/4	30.60	3-1/4	132.73	6-1/2	265.45
7/8	35.735	3-1/2	142.90	6-3/4	275.67
1	40.80	3-3/4	153.15	7	285.88
1-1/4	51.10	4	163.30	7-1/2	306.30
1-1/2	61.30	4-1/4	173.57	8	326.72
1-5/8	66.40	4-1/2	183.78	8-1/4	336.93
1-3/4	71.47	4-3/4	193.99	8-1/2	347.14
1-7/8	76.575	5	204.20	8-3/4	357.35
2	81.70	5-1/4	214.40	9	367.56
2-1/4	91.90	5-1/2	224.62		
2-1/2	102.10	5-3/4	234.83		

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

# AISI 4150 Hot Rolled Annealed

4150 grade is a medium-carbon, chromium-molybdenum steel. 4150 is also capable of good strength and wear resistance, has excellent toughness, good ductility and has the ability to resist stress and creep at prolonged high temperatures. In the annealed condition, machinability is improved.

Typical Analysis	AISI 4150
Carbon (C)	0.48 / 0.53
Manganese (Mn)	0.75 / 1.00
Phosphorus (P)	0.035 max
Sulphur (S)	0.02 / 0.04
Chromium (Cr)	0.80 / 1.10
Molybdenum (Mo)	0.15 / 0.25
Silicon (Si)	0.15 / 0.35
Nickel (Ni)	0.25 max
Copper (Cu)	0.35 max
Vanadium (V)	0.10 max
Aluminum (Al)	0.020 to 0.050
<b>Microstructure</b> - Steel to have a predominately lamellar pearlite structure for optimum machinability.	

Alloys &  
Tool Steel

Alro Steel Metals Guide



# AISI 4150 Hot Rolled Annealed Rounds

Diameter (inches)	Weight (lbs./foot)
2	10.680
2-1/8	12.234
2-1/4	13.704
2-3/8	15.258
2 -1/2	16.896
2-5/8	18.724
2-3/4	20.533
2-7/8	22.426
3	24.645
3-1/8	26.717
3-1/4	28.872
3-1/2	33.434
3-5/8	36.070

Diameter (inches)	Weight (lbs./foot)
3-3/4	38.568
4	43.814
4-1/8	46.562
4-1/4	49.394
4-1/2	55.309
4-3/4	61.859
5	68.459
5-1/4	75.393
5-1/2	82.661
5-3/4	91.359
6	99.343
6-1/4	107.662
6-1/2	116.315

Diameter (inches)	Weight (lbs./foot)
6-3/4	126.162
7	135.515
7-1/4	145.202
7-1/2	155.224
7-3/4	165.580
8	176.275
8-1/4	187.296
8-1/2	199.737
8-3/4	211.463
9	223.522
9-1/4	235.501
9-1/2	248.207
10	277.171

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Stock Lengths: 20 foot randoms

## AISI 4150R Gun Barrel Quality Rounds

This 4150 HR GBQ is a unique grade now stocked at Alro Steel. It has been designed to provide superior performance for use specifically in the firearm industry. Features of 4150 GBQ include superior performance for gun barrel drilling, reaming, and machining. There is also less distortion to the gun-drilled surface. Being a product made for a specific end-use market, Please contact a member of the Alro Steel Bar Group in Corporate Purchasing if you have any questions or need any additional information.

Diameter (inches)	Weight (lbs./foot)
1.000	2.67
1.032	2.84
1.063	3.014
1.125	3.38
1.250	4.17

### Typical Applications

Production of handgun, rifle and shotgun barrels, as well as other firearm components.

### Specifications

- Meets MIL-B-11595E.
- Grade: 4150R.
- Condition: Quench & Tempered.
- Finishes: Hot Rolled as Rolled or Turned and Polished



# AISI 4150R Q&T SR Hot Rolled

(Resulphurized, Hot Rolled, Quenched and Tempered, Stress Relieved)

4150R HR Q&T SR is a free-machining alloy steel that provides an outstanding combination of heat treated properties and superior machinability. This alloy steel is manufactured under close quality control for uniformity to an ASTM grain size of 5 to 8. It is especially suitable for service applications where substantial strength, toughness and hardness are required.

Typical Analysis	AISI 4150R
Carbon (C)	0.47 / 0.55
Manganese (Mn)	0.75 / 1.35
Silicon (Si)	0.15 / 0.30
Molybdenum (Mo)	0.15 / 0.25
Chromium (Cr)	0.70 / 1.10
Sulphur (S)	0.06 / 0.10
Phosphorus (P)	0.035 max.
Tensile Strength	approx. 110,000 lbs psi
Yield Point	approx. 85,000 lbs psi
Brinell Hardness	269 - 341
Elongation in 2"	16%
Reduction in Area	51%
Rounds 11" and up are not resulphurized.	
Flats and Squares Hot rolled, heat treated, machine straightened, stress relieved. BHN 269/321	

Alloys &  
Tool Steel

## AISI 4150R Q&T SR Hot Rolled Rounds

Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)
3/4	1.500	3-5/8	36.070	8-3/4	211.463
7/8	2.040	3-3/4	38.568	9	223.522
1	2.676	4	43.814	9-1/4	235.501
1-1/8	3.384	4-1/8	46.562	9-1/2	248.207
1-1/4	4.176	4-1/4	49.394	10	277.171
1-3/8	5.052	4-1/2	55.309	10-1/2	305.044
1-1/2	6.012	4-3/4	61.859	11	334.253
1-5/8	7.056	5	68.459	11-1/2	364.796
1-3/4	8.172	5-1/4	75.393	12	396.675
1-7/8	9.384	5-1/2	82.661	12-1/2	429.889
2	10.680	5-3/4	91.359	13	466.624
2-1/8	12.234	6	99.343	13-1/2	502.591
2-1/4	13.704	6-1/4	107.662	14	539.893
2-3/8	15.258	6-1/2	116.315	14-1/2	573.511
2 -1/2	16.896	6-3/4	126.162	15	618.503
2-5/8	18.724	7	135.515	16	702.454
2-3/4	20.533	7-1/4	145.202	17	791.746
2-7/8	22.426	7-1/2	155.224	18	886.378
3	24.645	7-3/4	165.580	19	986.351
3-1/8	26.717	8	176.275	20	1091.664
3-1/4	28.872	8-1/4	187.296	22	1318.314
3-1/2	33.434	8-1/2	199.737		

Please refer to pages 8-32 thru 8-34 for alloy tolerances.  
Rounds 12" and up are not resulphurized. Stock lengths 20' randoms

Alro Steel Metals Guide



# 4150 Dybar - (MOD) RS Hot Rolled

4150 Dybar is a special quality alloy steel that has been resulphurized for considerations for machining. Modifications have been made to the chemical composition for increased hardenability. This steel is made by a single slab electric furnace process to a silicon fully killed practice and resulphurized to set limits.

Typical Analysis	AISI 4150
Carbon (C)	0.47 / 0.55
Manganese (Mn)	0.95 / 1.30
Silicon (Si)	0.20 / 0.35
Molybdenum (Mo)	0.15 / 0.25
Chromium (Cr)	0.60 / 0.90
Vanadium (V)	0.10 max.
Sulphur (S)	0.06 / 0.10
Phosphorus (P)	0.025 max.
Nickel (Ni)	0.25 max.
Columbium	0.015 / 0.035

## 4150 Dybar - (MOD) RS HR Flats & Squares

Size (inches)	Weight (lbs./foot)
<b>5/8 x</b>	
2-1/2	5.471
3	6.566
4-1/2	9.848
<b>1 x</b>	
2-1/2	8.755
3-1/2	12.250
4-1/2	15.759
<b>1-1/8 x</b>	
2-1/2	9.848
3-1/2	13.788
4-1/2	17.728
5	19.698
8	31.550
<b>1-1/4 x</b>	
2-1/2	10.943
3-1/2	15.321
4	17.510
4-1/2	19.698
5	21.887
7	30.670

Size (inches)	Weight (lbs./foot)
<b>1-1/2 x</b>	
2-1/2	13.132
3	15.759
3-1/2	18.385
4	21.012
4-1/2	23.638
5	26.265
6	31.518
7	36.810
8	42.024
<b>1-3/4 x</b>	
3-1/4	19.940
<b>2 x</b>	
2-1/2	17.510
3	21.012
3-1/2	24.514
4	28.016
4-1/2	31.518
5	35.050
6	42.060
8	56.080

Size (inches)	Weight (lbs./foot)
<b>2-1/2 x</b>	
2-1/2	21.887
3	26.265
3-1/2	30.642
4	35.020
4-1/2	39.397
6	52.530
<b>3 x</b>	
3	31.518
4	42.024
5	52.530
6	63.036
<b>3-1/2 x</b>	
3-1/2	42.899
<b>4 x</b>	
4	56.040
8	112.170
<b>4-5/8 x 4-5/8</b>	74.065
<b>5-1/8 x 5-1/8</b>	93.666
<b>5-5/8 x 5-5/8</b>	112.652
<b>6-1/8 x 6-1/8</b>	133.085

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

# AISI 4340

## Annealed, Hot Rolled

4340 is a highly alloyed steel with high nickel and chromium content which assures deep hardening when oil quenched, with high strength characteristics throughout the section. Used for heavily stressed parts operating under strenuous conditions.

Typical Analysis	AISI 4340
Carbon (C)	0.38 / 0.43
Manganese (Mn)	0.60 / 0.80
Silicon (Si)	0.15 / 0.35
Molybdenum (Mo)	0.20 / 0.30
Chromium (Cr)	0.70 / 0.90
Nickel (Ni)	1.65 / 2.00
Sulphur (S)	0.040 max.
Phosphorus (P)	0.035 max.

# AISI 4340

## Q&T (For Reference Only), Hot Rolled

Typical Analysis	AISI 4340
Carbon (C)	0.38 / 0.43
Manganese (Mn)	0.60 / 0.80
Silicon (Si)	0.15 / 0.35
Molybdenum (Mo)	0.20 / 0.30
Chromium (Cr)	0.70 / 0.90
Nickel (Ni)	1.65 / 2.00
Sulphur (S)	0.040 max.
Phosphorus (P)	0.035 max.
<b>Tensile Strength</b>	approx. 130,000 lbs psi
<b>Yield Point</b>	approx. 100,000 lbs psi
<b>Brinell Hardness</b>	285 - 363
<b>Elongation in 2"</b>	approx. 14%
<b>Reduction in Area</b>	approx. 35%

*Note: Mechanical Properties for Q&T are for reference only!*

# AISI 4340 - HR Q&T Rounds

Diameter (inches)	Weight (lbs./foot)
1	2.670
1-1/8	3.379
1-1/4	4.170
1-3/8	5.048
1-1/2	6.010
1-5/8	7.050
1-3/4	8.180
1-7/8	9.387
2	10.680
2-1/8	12.234
2-1/4	13.704
2-3/8	15.258
2-1/2	16.896
2-5/8	18.724
2-3/4	20.533
2-7/8	22.426
3	24.645
3-1/8	26.717
3-1/4	28.872

Diameter (inches)	Weight (lbs./foot)
3-1/2	33.434
3-3/4	38.568
4	43.814
4-1/4	49.394
4-1/2	55.309
4-3/4	61.859
5	68.459
5-1/4	75.393
5-1/2	82.661
5-3/4	91.359
6	99.343
6-1/4	107.662
6-1/2	116.315
6-3/4	126.162
7	135.515
7-1/4	145.202
7-1/2	155.224
7-3/4	165.580
8	176.275

Diameter (inches)	Weight (lbs./foot)
8-1/4	187.296
8-1/2	199.737
9	223.522
9-1/2	248.207
10	277.171
10-1/2	305.044
11	334.253
11-1/2	364.796
12	396.675
13	466.624
14	539.893
15	618.503
16	702.454
17	791.746
18	886.378
19	986.351
20	1091.664

*Rounds over 12" are Forged, Rough Turned, Q&T*

# AISI 4340 - Annealed Rounds

Diameter (inches)	Weight (lbs./foot)
3/4	1.500
7/8	2.040
1	2.676
1-1/8	3.384
1-1/4	4.176
1-3/8	5.052
1-1/2	6.012
1-5/8	7.056
1-3/4	8.172
1-7/8	9.384
2	10.680
2-1/8	12.234
2-1/4	13.704
2-3/8	15.258
2-1/2	16.896
2-3/4	20.533
3	24.645
3-1/4	28.872
3-1/2	33.434

Diameter (inches)	Weight (lbs./foot)
3-3/4	38.568
4	43.814
4-1/8	46.562
4-1/4	49.394
4-1/2	55.309
4-5/8	58.685
4-3/4	61.859
5	68.459
5-1/4	75.393
5-1/2	82.661
5-3/4	91.359
6	99.343
6-1/4	107.662
6-1/2	116.315
6-3/4	126.162
7	135.515
7-1/2	155.224
8	176.275
8-1/4	187.296

Diameter (inches)	Weight (lbs./foot)
8-1/2	199.737
9	223.522
9-1/4	235.501
9-1/2	248.207
10	277.171
10-1/2	305.044
11	334.253
11-1/2	364.796
12	396.675
12-1/2	429.889
13	466.624
13-1/2	502.591
14	539.893
15	618.503
16	702.454
17	791.746
18	886.378
20	1091.664

*Rounds 1/2" - 11" are Hot Rolled Annealed. Rounds over 11" are Forged, Rough Turned, Annealed. Please refer to pages 8-32 thru 8-34 for alloy tolerances. Stock Lengths: 20 foot randoms*

# AISI 4340

## Annealed Aircraft Quality (AQ) Rounds

<b>AISI</b>	<b>4340 CFA-AQ</b>	<b>4340 HRA-AQ</b>
<b>ASTM</b>	<b>A108, A331</b>	<b>A322, A304, E381</b>
<b>AMS</b>	<b>6415</b>	<b>6415</b>

Diameter (inches)	Weight (lbs./foot)	4340 CFA-AQ	4340 HRA-AQ
1/2	.668	●	
3/4	1.500	●	
1	2.676	●	
1-1/4	4.176	●	
1-1/2	6.012	●	
1-3/4	8.172	●	
2	10.680	●	
2-1/4	13.704	●	
2-1/2	16.896	●	
2-3/4	20.533	●	
3	24.645	●	●
3-1/4	28.872		●
3-1/2	33.434		●
3-3/4	38.568		●
4	43.814		●
4-1/4	49.394		●
4-1/2	55.309		●
4-3/4	61.859		●
5	68.459		●
5-1/2	82.661		●
6	99.343		●
6-1/2	116.315		●
7	135.515		●
7-1/2	155.224		●
8	176.275		●
8-1/2	199.737		●
9	223.522		●
9-1/2	248.207		●
10	277.171		●

**Alloys &  
Tool Steel**

**Alro Steel Metals Guide**



# AISI 6150 - Annealed, HR/DCF

An electric furnace melt of chrome vanadium steel possessing the following characteristics: oil-hardening, high resistance to vibratory stress, standard deformation, medium hardness, high torque strength and bright polish.

## Typical Applications

Arbors, Heavy Machinery Parts, Gears, Shafts, High Strength Studs and Spindles.

Typical Analysis	AISI 6150
Carbon (C)	0.48 / 0.53
Manganese (Mn)	0.70 / 0.90
Silicon (Si)	0.15 / 0.30
Phosphorus (P)	0.035 max.
Sulphur (S)	0.040 max.
Molybdenum (Mo)	
Chromium (Cr)	0.80 / 1.10
Vanadium (V)	0.15 min.
Cobalt (Co)	
<b>Forging (a)</b> Start forging at Do not forge below	1750 - 2150°F (950 - 1175°C) 1600° F (870°C)
<b>Normalizing (b)</b>	1650 - 1700°F (899 - 927°C)
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1525 - 1575°F (828 - 855°C)  179 - 217
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly  1500 - 1550°F (816 - 843°C)  O (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	400°F (204°C)  56 - 58
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	Low
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	Medium
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Medium
<b>Safety in Hardening</b>	Low
<b>Resistance to Carburization</b>	Medium

# AISI 6150 - Annealed Flats & Squares

## DCF (Cut From Plate)

Size (inches)	Weight (lbs./foot)
<b>1/2 x</b>	
1/2	1.031
5/8	1.254
3/4	1.478
1	1.924
1-1/4	2.371
1-1/2	2.818
1-3/4	3.264
2	3.711
2-1/4	4.158
2-1/2	4.604
2-3/4	5.051
3	5.498
3-1/2	6.391
4	7.284
5	9.071
6	10.858
8	14.431
10	18.004
12	23.849
16	31.717
20	39.585
24	47.453
<b>5/8 x</b>	
5/8	1.553
3/4	1.829
1	2.382
1-1/4	2.935
1-1/2	3.488
1-3/4	4.041
2	4.594
2-1/4	5.148
2-1/2	5.701
2-3/4	6.254
3	6.807
3-1/2	7.913
4	9.019
4-1/2	10.125
5	11.231
5-1/2	12.337
6	13.443
7	15.655
8	17.867
9	20.079
10	22.291
12	29.006
16	38.576
20	48.146
24	57.715
32	76.855

Size (inches)	Weight (lbs./foot)
<b>3/4 x</b>	
3/4	2.181
1	2.841
1-1/4	3.500
1-1/2	4.159
1-3/4	4.819
2	5.478
2-1/4	6.137
2-1/2	6.797
2-3/4	7.456
3	8.116
3-1/2	9.434
4	10.753
5	13.390
6	16.028
8	21.303
10	26.578
12	34.164
16	45.435
20	56.706
24	67.978
32	90.521
<b>1 x</b>	
1	3.757
1-1/4	4.629
1-1/2	5.501
1-3/4	6.373
2	7.245
2-1/4	8.117
2-1/2	8.989
2-3/4	9.861
3	10.733
3-1/2	12.478
4	14.222
4-1/2	15.966
5	17.710
6	21.198
7	24.687
8	28.175
10	35.151
12	44.479
16	59.153
20	73.828
24	88.503
32	117.852
<b>1-1/8x</b>	
2-1/2	10.086
4-1/2	17.913
<b>1-1/4 x</b>	
1-1/4	5.758
1-1/2	6.843
1-3/4	7.927

Size (inches)	Weight (lbs./foot)
<b>1-1/4 x</b>	
2	9.012
2-1/4	10.097
2-1/2	11.182
2-3/4	12.267
3	13.351
3-1/2	15.521
4	17.690
4-1/2	19.860
5	22.030
6	26.369
8	35.047
10	43.725
12	54.794
16	72.872
20	90.949
24	109.027
32	145.183
<b>1-3/8 x</b>	
1-3/8	6.918
1-1/2	7.514
1-3/4	8.705
2	9.896
2-1/4	11.087
2-1/2	12.278
2-3/4	13.469
3	14.660
3-1/2	17.043
4	19.425
5	24.189
6	28.954
8	38.483
10	48.012
12	59.951
16	79.731
20	99.510
24	119.290
32	158.848
<b>1-1/2 x</b>	
1-1/2	8.184
1-3/4	9.290
2	10.587
2-1/4	11.885
2-1/2	13.182
2-3/4	14.480
3	15.803
3-1/2	18.372
4	20.967
4-1/2	23.562
5	26.157
6	31.347

**Alloys &  
Tool Steel**

**Alro Steel Metals Guide**

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Note, sizes not listed above can be cut from plate.

Continued on next page

# AISI 6150 - Annealed Flats & Squares

## DCF (Cut From Plate)

Alloys &  
Tool Steel

Alro Steel Metals Guide

Size (inches)	Weight (lbs./foot)
<b>1-1/2 x</b>	
8	41.727
10	52.106
12	65.109
16	83.246
20	104.005
24	127.765
32	166.284
<b>1-3/4 x</b>	
1-3/4	11.036
2	12.546
3	18.587
3-1/2	21.608
4	24.628
4-1/2	27.648
5	30.669
5-1/2	33.689
6	36.709
7	42.750
8	48.791
9	54.831
10	60.872
12	75.424
16	100.308
20	125.192
24	150.077
32	199.845
<b>2 x</b>	
2	14.314
2-1/4	16.036
2-1/2	17.759
2-3/4	19.482
3	21.205
3-1/2	24.651
4	28.097
4-1/2	31.542
5	34.988
6	41.880
8	55.662
10	69.445
12	85.739
16	114.027
20	142.314
24	170.601
32	227.176

Size (inches)	Weight (lbs./foot)
<b>2-1/2 x</b>	
2-1/2	22.144
2-3/4	24.293
3	26.441
3-1/2	30.737
4	35.034
5	43.627
6	52.220
8	69.406
10	86.592
12	106.369
16	141.463
20	176.557
24	211.651
<b>3 x</b>	
3	31.677
3-1/2	36.824
4	41.971
5	52.266
6	62.561
8	83.150
10	103.739
12	127.000
14	147.950
16	168.900
20	210.800
24	252.700
32	336.500
<b>3-1/2 x</b>	
3-1/2	42.911
4	48.909
5	60.905
6	72.901
8	96.894
10	120.887
12	147.630
16	196.336
20	245.043
24	293.749
32	391.163

Size (inches)	Weight (lbs./foot)
<b>4 x</b>	
4	55.846
5	69.544
6	83.242
8	110.638
10	138.034
12	168.260
14	196.016
16	223.773
20	279.286
24	334.799
32	445.825
<b>4-1/2 x</b>	
4-1/2	72.041
5	79.831
6	95.411
8	126.571
10	157.730
12	188.890
16	251.209
20	313.529
24	375.848
32	500.487
<b>5 x</b>	
5	88.550
6	105.832
8	140.394
10	174.957
12	209.520
16	278.646
20	347.772
24	416.898
32	555.149
<b>6 x</b>	
6	126.673
8	168.042
10	209.411
12	250.781
16	333.519
20	416.258
24	498.996
32	664.474

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Note, sizes not listed above can be cut from plate.





# AISI 6150 - Annealed HR Rounds

Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)
1	2.676	3-3/4	38.175	8	174.251
1-1/8	3.384	4	43.394	8-1/4	185.204
1-1/4	4.176	4-1/4	48.939	8-1/2	197.178
1-3/8	5.052	4-1/2	54.822	8-3/4	208.818
1-1/2	6.012	4-3/4	61.243	9	220.816
1-5/8	7.056	5	67.804	9-1/4	235.501
1-3/4	8.180	5-1/4	74.699	9-1/2	248.207
1-7/8	9.390	5-1/2	81.928	10*	277.171
2	10.680	5-3/4	90.203	10-1/2*	305.044
2-1/8	12.230	6	98.146	11*	334.253
2-1/4	13.704	6-1/4	103.390	11-1/2*	364.796
2-1/2	16.896	6-1/2	114.985	12*	396.675
2-5/8	18.724	6-3/4	123.078	13*	466.624
2-3/4	20.533	7	133.771	14*	539.893
3	24.409	7-1/4	143.397	15*	618.503
3-1/4	28.606	7-1/2	153.348	16*	702.454
3-1/2	33.143	7-3/4	163.633		

Diameter tolerance may vary depending on sourcing.  
Stock Lengths: 20 foot randoms

\* Over 10" is forged

Alloys &  
Tool Steel

Alro Steel Metals Guide



# AISI 8620/86L20

Carefully controlled proportions of chromium, nickel and molybdenum are responsible for the extensive use of 8620 as a carburizing alloy steel. Valuable features of this grade include extreme surface hardenability and internal strength.

Typical Analysis	AISI 8620 / 86L20
Carbon (C)	0.18 / 0.23
Manganese (Mn)	0.70 / 0.90
Silicon (Si)	0.15 / 0.30
Nickel (Ni)	0.40 / 0.70
Molybdenum (Mo)	0.15 / 0.25
Chromium (Cr)	0.40 / 0.60
Phosphorus (P)	0.035 MAX
Sulphur (S)	0.040 MAX
*Lead	0.15 / 0.35

*\*Applies only to 8620 leaded alloy steel bars.*

# AISI 8620 Flats and Squares

## HR (Cut From Plate)

Size (inches)	Weight (lbs./foot)	Size (inches)	Weight (lbs./foot)	Size (inches)	Weight (lbs./foot)
<b>3/8 x</b>	3/8	0.594	<b>5/8 x</b>	2-1/4	5.114
	1/2	0.765		2-1/2	5.667
	5/8	0.935		2-3/4	6.220
	3/4	1.105		3	6.773
	1	1.446		3-1/2	7.879
	1-1/4	1.786		4	8.985
	1-1/2	2.126		4-1/2	10.092
	1-3/4	2.467		5	11.198
	2	2.807		6	13.410
	2-1/4	3.147		8	17.834
	2-1/2	3.488		10	22.257
	2-3/4	3.827		12	26.682
	3	4.168		16	35.530
	3-1/2	4.849		20	44.378
	4	5.530		24	53.227
	6	8.252	<b>3/4 x</b>	3/4	2.141
<b>1/2 x</b>	1/2	1.004		1	2.801
	5/8	1.227		1-1/4	3.460
	3/4	1.451		1-1/2	4.120
	1	1.897		1-3/4	4.779
	1-1/4	2.344		2	5.438
	1-1/2	2.791		2-1/4	6.098
	1-3/4	3.237		2-1/2	6.757
	2	3.684		2-3/4	7.417
	2-1/4	4.131		3	8.076
	2-1/2	4.577		3-1/2	9.395
	2-3/4	5.024		4	10.713
	3	5.471		4-1/2	12.032
	3-1/2	6.364		5	13.351
	4	7.257		6	15.988
	4-1/2	8.151		8	21.263
	5	9.044		10	26.538
	6	10.831		12	31.813
	7	12.618		16	42.363
	8	14.404		20	52.913
	10	17.978		24	63.463
	12	21.551	<b>1 x</b>	1	3.704
	16	28.697		1-1/8	4.141
	20	35.844		1-1/4	4.577
	24	42.991		1-1/2	5.449
<b>5/8 x</b>	5/8	1.520		1-3/4	6.321
	3/4	1.796		2	7.193
	1	2.349		2-1/4	8.065
	1-1/4	2.902		2-1/2	8.937
	1-1/2	3.455		2-3/4	9.809
	1-3/4	4.008		3	10.681
	2	4.561		3-1/2	12.425
<b>1 x</b>	4	14.169	<b>1-1/4 x</b>	1-1/4	5.692
	4-1/2	15.914		1-1/2	6.778
	5	17.658		1-3/4	7.862
	6	21.146		2	8.947
	8	28.123		2-1/4	10.032
	10	35.099		2-1/2	11.117
	12	42.076		2-3/4	12.201
	16	56.028		3	13.286
	20	69.981		3-1/2	15.456
	24	83.934		4	17.625
<b>1-1/2 x</b>	1-1/2	8.106		4-1/2	19.795
	2	10.702		5	21.964
	2-1/4	11.999		6	26.304
	2-1/2	13.296		8	34.982
	2-3/4	14.594		10	43.660
	3	15.891		12	52.338
	3-1/2	18.486		16	69.694
	4	21.081		20	87.050
	4-1/2	23.676		24	104.406
	5	26.271	<b>1-1/2 x</b>	1-1/2	8.106
	6	31.461		2	10.702
	8	41.841		2-1/4	11.999
	10	52.221		2-1/2	13.296
	12	62.600		2-3/4	14.594
	16	83.359		3	15.891
	20	104.119		3-1/2	18.486
	24	124.878		4	21.081
				4-1/2	23.676
				5	26.271

Please refer to pages 8-32 thru 8-34 for alloy tolerances.

Note, sizes not listed above can be cut from plate, please inquire.

Weights above include nominal oversize tolerance. Actual weights may vary.

Alloys &  
Tool Steel

Alro Steel Metals Guide

Continued on next page

# AISI 8620 Flats and Squares

**HR (Cut From Plate)**

**Alloys &  
Tool Steel**

**Alro Steel Metals Guide**

Size (inches)	Weight (lbs./foot)
<b>1-3/4 x</b>	
1-3/4	10.945
2	12.456
2-1/2	15.476
3	18.497
4	24.537
4-1/2	27.557
5	30.578
6	36.619
8	48.700
10	60.781
12	72.862
16	97.025
20	121.188
24	145.350
<b>2 x</b>	
2	14.210
2-1/4	15.933
2-1/2	17.656
2-3/4	19.379
3	21.102
3-1/2	24.547
4	27.993
4-1/2	31.438
5	34.885
6	41.776
8	55.559
9	62.451
10	69.342
12	83.125
16	110.690
20	138.257
24	165.822

Size (inches)	Weight (lbs./foot)
<b>2-1/4 x</b>	
2-1/4	17.900
2-1/2	19.836
2-3/4	21.771
3	23.707
3-1/2	27.578
4	31.449
4-1/2	35.320
5	39.191
5-1/2	43.063
6	46.934
8	62.418
10	77.903
12	93.387
16	124.357
20	155.326
24	165.823
<b>2-1/2 x</b>	
2-1/2	22.015
2-3/4	24.164
3	26.312
3-1/2	30.609
4	34.905
4-1/2	39.202
5	43.498
5-1/2	47.795
6	52.091
8	69.277
10	86.464
12	103.650
16	138.022
20	172.394
24	206.767

Size (inches)	Weight (lbs./foot)
<b>3 x</b>	
3	31.522
3-1/2	36.670
4	41.817
4-1/2	46.964
5	52.112
6	62.406
8	82.996
10	103.585
12	124.174
16	165.353
20	206.532
24	247.711
<b>3-1/2 x</b>	
3-1/2	42.730
4	48.525
4-1/2	54.523
5	60.521
5-1/2	66.723
6	72.518
8	96.510
10	120.502
12	144.495
16	192.480
20	240.465
24	288.451
<b>4 x</b>	
4	55.408
4-1/2	62.257
5	69.106
5-1/2	75.955
6	82.804
8	110.199
10	137.595
12	164.991
16	219.782
20	274.574
24	329.366

*Please refer to pages 8-32 thru 8-34 for alloy tolerances.*

*Note, sizes not listed above can be cut from plate.*



# AISI 8620 HR Rounds

Diameter (inches)	Weight (lbs./foot)
5/8	1.044
3/4	1.500
7/8	2.040
1	2.676
1-1/16	3.01
1-1/8	3.384
1-3/16	3.76
1-1/4	4.176
1-5/16	4.60
1-3/8	5.052
1-7/16	5.52
1-1/2	6.012
1-5/8	7.056
1-3/4	8.172
1-7/8	9.384
2	10.680
2-1/8	12.234
2-1/4	13.704
2-3/8	15.258
2-1/2	16.896
2-5/8	18.724
2-3/4	20.533
2-7/8	22.426
3	24.645

Diameter (inches)	Weight (lbs./foot)
3-1/8	26.717
3-1/4	28.872
3-1/2	33.434
3-5/8	36.070
3-3/4	38.568
4	43.814
4-1/8	46.562
4-1/4	49.394
4-1/2	55.309
4-3/4	61.859
5	68.459
5-1/4	75.393
5-1/2	82.661
5-3/4	91.359
6	99.343
6-1/4	107.662
6-1/2	116.315
6-3/4	126.162
7	135.515
7-1/4	145.202
7-1/2	155.224
7-3/4	165.580
8	176.271
8-1/4	187.296

Diameter (inches)	Weight (lbs./foot)
8-1/2	199.737
8-3/4	211.463
9	223.522
9-1/4	235.501
9-1/2	248.207
9-3/4	253.812
10	277.171
10-1/4	290.941
10-1/2	305.044
11	334.253
11-1/2	364.796
12	396.675
12-1/2	429.889
13	466.624
14	539.893
15	618.503
16	702.454
17	791.746
18	886.378
19	986.351
20	1091.664
22	1318.314
24	1566.326
26	1835.701

Please refer to pages 8-32 thru 8-34 for alloy tolerances.  
Stock Lengths: 18 - 20 foot randoms

Alloys & Tool Steel

# AISI 8620 CF Rounds

Diameter (inches)	Weight (lbs./foot)
1/4	0.167
5/16	0.261
3/8	0.375
7/16	0.511
1/2	0.668
9/16	0.845
5/8	1.043
11/16	1.262
3/4	1.502
13/16	1.763
7/8	2.044
15/16	2.347
1	2.670
1-1/16	3.014
1-1/8	3.379

Diameter (inches)	Weight (lbs./foot)
1-3/16	3.765
1-1/4	4.172
1-5/16	4.599
1-3/8	5.048
1-7/16	5.517
1-1/2	6.008
1-5/8	7.050
1-3/4	8.177
1-7/8	9.387
2	10.680
2-1/8	12.057
2-1/4	13.517
2-3/8	15.060
2-1/2	16.688
2-5/8	18.398

Diameter (inches)	Weight (lbs./foot)
2-3/4	20.192
2-7/8	22.069
3	24.030
3-1/8	26.074
3-1/4	28.202
3-3/8	30.413
3-1/2	32.708
3-3/4	37.547
4	42.720
4-1/4	48.227
4-1/2	54.068
4-3/4	60.242
5	66.750
6	96.120

Please refer to pages 8-32 thru 8-34 for alloy tolerances.  
Stock Lengths: 12 foot (20 foot also available in most sizes).

Alro Steel Metals Guide

# AISI 86L20 CF Rounds

Diameter (inches)	Weight (lbs./foot)
3/8	0.38
1/2	0.67
9/16	0.85
5/8	1.04
3/4	1.50
13/16	1.76
7/8	2.04
15/16	2.35
1	2.67
1-1/8	3.38

Diameter (inches)	Weight (lbs./foot)
1-1/4	4.17
1-5/16	4.60
1-3/8	5.05
1-7/16	5.52
1-1/2	6.01
1-5/8	7.05
1-3/4	8.18
1-7/8	9.39
2	10.68
2-1/8	12.06

Diameter (inches)	Weight (lbs./foot)
2-1/4	13.52
2-3/8	15.06
2-1/2	16.69
2-5/8	18.40
2-3/4	20.19
3	24.03
3-1/4	28.20
3-1/2	32.71

# AISI 8620 HR Plate

Thickness (inches)	Weight (lbs./sqft)
1/2	20.4
3/4	30.6
1	40.8
1-1/8	45.9
1-1/4	51.0
1-1/2	61.2
1-3/4	71.47

Thickness (inches)	Weight (lbs./sqft)
2	81.6
2-1/4	91.89
2-1/2	102.0
2-3/4	112.31
3	122.4
3-1/2	142.9
4	163.3

Refer to pages 8-32 thru 8-34 for alloy tolerances.

# AISI 52100

AISI 52100 is a moderately deep hardening alloy having high resistance to wear, medium toughness, and low resistance to softening at high temperatures.

Typical Analysis	AISI 52100
Carbon (C)	0.98 / 1.10
Manganese (Mn)	0.25/ 0.45
Silicon (Si)	0.15 - 0.30
Chromium (Cr)	1.30 / 1.60
Phosphorus (P)	0.025 MAX
Sulphur (S)	0.025 MAX
Physical Properties	
Contact Alro for specific certification.	

Alloys &  
Tool Steel

## AISI 52100 Rounds

Spheroidize Annealed, B.Q.

Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)
3/8	0.380	2	10.680	5-1/4	73.590
1/2	0.667	2-1/4	13.512	5-1/2	80.767
5/8	1.042	2-3/8	15.060	6	96.120
3/4	1.501	2-1/2	16.687	6-1/4	104.296
13/16	1.760	2-5/8	18.400	6-1/2	112.807
7/8	2.044	2-3/4	20.191	6-3/4	123.078
1	2.670	3	24.030	7	130.830
1-1/8	3.379	3-1/4	28.201	7-1/2	150.187
1-1/4	4.171	3-1/2	32.710	8	170.880
1-3/8	5.047	3-3/4	37.547	8-1/2	197.178
1-1/2	6.007	4	42.720	9	220.816
1-5/8	7.050	4-1/4	48.230	10	277.171
1-3/4	8.176	4-1/2	54.067	11	334.253
1-13/16	8.780	4-3/4	60.240	12	396.675
1-7/8	9.386	5	66.750		

Diameter tolerance may vary depending on sourcing.

Alro Steel Metals Guide



# Hot Rolled Alloy Bars

## Size Tolerances and Out-of-Round or Out-of Square Tolerances

Hot Rolled Alloy Bars Round, Square and Round-Cornered Square			
Specified Sizes (inches)	Size Tolerances (inches)		Out-of-Round or Out-of-Square Section (inches)
	Over	Under	
Up thru 5/16	0.005	0.005	0.008
Over 5/16 thru 7/16	0.006	0.006	0.009
Over 7/16 thru 5/8	0.007	0.007	0.010
Over 5/8 thru 7/8	0.008	0.008	0.012
Over 7/8 thru 1	0.009	0.009	0.013
Over 1 thru 1-1/8	0.010	0.010	0.015
Over 1-1/8 thru 1-1/4	0.011	0.011	0.016
Over 1-1/4 thru 1-3/8	0.012	0.012	0.018
Over 1-3/8 thru 1-1/2	0.014	0.014	0.021
Over 1-1/2 thru 2	1/64	1/64	0.023
Over 2 thru 2-1/2	1/32	0	0.023
Over 2-1/2 thru 3-1/2	3/64	0	0.035
Over 3-1/2 thru 4-1/2	1/16	0	0.046
Over 4-1/2 thru 5-1/2	5/64	0	0.058
Over 5-1/2 thru 6-1/2	1/8	0	0.070
Over 6-1/2 thru 8-1/4	5/32	0	0.085
Over 8-1/4 thru 9-1/2	3/16	0	0.100
Over 9-1/2 thru 10	1/4	0	0.120

Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same transverse cross section. Out-of-square section is the difference in perpendicular distance between opposite faces, measured at the same transverse cross section.

## Size Tolerances - Rounds

Turned, Ground & Polished	
Diameter Range (inches)	Heat Treated
Up thru 1-1/2	+0 - 0.0015
Over 1-1/2 thru 2-1/2	+0 - 0.0020
Over 2-1/2 thru 3	+0 - 0.0025
Over 3 thru 4	+0 - 0.0035
Over 4 thru 6	+0 - 0.0045



# Straightness \*Tolerances - Steel Bars

## Hot Rolled Bars

Straightness is a perishable tolerance; therefore, reasonable care in handling and storage should be taken to avoid bending the bars. Deviation from straightness is measured by placing the bar on a level table so that the arc or deviation from straightness is horizontal, and the depth of the arc is measured with a steel scale and a straight edge. A tightly-stretched string can be used as a substitute for a steel scale.

<b>Hot Rolled Bars</b>	1/4" in any 5 ft. or $1/4 \times \frac{\text{no. of ft. of length}}{5}$ inches
<b>Hot Rolled, Thermally Treated</b>	1/4" in any 5 ft. or $1/4 \times \frac{\text{no. of ft. of length}}{5}$ inches

\* There is not a published flatness or straightness tolerance for flat bars.

# Straightness \*Tolerances - Steel Bars

## Cold Finished Bars

Form Size (inches)	Length (feet)	Maximum Curvature (Depth of arc in inches)
<b>Rounds</b>		
<b>Less than .28 Carbon</b>		
Less than 5/8"	Less than 15'	1/8" in any 10' portion of the total length
Less than 5/8"	15' and over	1/8" in any 10' portion of the total length
5/8" and over	Less than 15'	1/16" in any 10' portion of the total length
5/8" and over	15' and over	1/8" in any 10' portion of the total length
<b>.28 Carbon and over and all heat treated material</b>		
Less than 5/8"	Less than 15'	3/16" in any 10' portion of the total length
Less than 5/8"	15' and over	5/16" in any 10' portion of the total length
5/8" and over	Less than 15'	1/8" in any 10' portion of the total length
5/8" and over	15' and over	3/16" in any 10' portion of the total length
<b>Hexagons &amp; Squares</b>		
<b>Less than .28 Carbon</b>		
Less than 5/8"	Less than 15'	3/16" in any 10' portion of the total length
Less than 5/8"	15' and over	5/16" in any 10' portion of the total length
5/8" and over	Less than 15'	1/8" in any 10' portion of the total length
5/8" and over	15' and over	3/16" in any 10' portion of the total length
<b>.28 Carbon and over and all heat treated material</b>		
Less than 5/8"	Less than 15'	1/4" in any 10' portion of the total length
Less than 5/8"	15' and over	3/8" in any 10' portion of the total length
5/8" and over	Less than 15'	3/16" in any 10' portion of the total length
5/8" and over	15' and over	1/4" in any 10' portion of the total length

\* There is not a published flatness or straightness tolerance for flat bars.

# Thickness & Width Oversize Ranges

## De-Carb Free Flats and Squares

Size (inches)	Width - Based on Thickness (inches)	Thickness (inches)
Through 4" thick	+.035 / +.077 oversize	+.015 / +.035 oversize
Rough Milled 4" thru <5"	+.062 / +.124 oversize	+.062 / +.125 oversize
Rough Milled 5" and over	+.062 / +.124 oversize	+.125 / +.250 oversize

## Thickness Tolerances

### 4140 HRA and 8620 HR Flats

All widths range from .035 - .124 oversize

Thickness (inches)	Tolerance
3/8 .....	+.03 -.01
1/2 .....	+.03 -.01
5/8 .....	+.04 -.01
3/4 and 7/8 .....	+.04 -.01
1 to 1-7/8 .....	+.07 -.01
2 to 2-3/4 .....	+.11 -.01
3 to 3-3/4 .....	+.13 -.01
4 to 4-1/2 .....	+.15 -.01

## Standard Manufacturing Tolerances

### Cold Finished Alloy Bars (Undersize variation in inches)

Size & Shape	Maximum of Carbon Range .28% or less	Maximum of Carbon over .28% thru .55%	Max. Carbon thru .55%, Stress Rel or Annealed after Cold Finishing	Max. Carbon over .55% or All Carbons Heat Treated	E.T.D. 150°
<b>Rounds (Cold Drawn or Turned and Polished)</b>					
Up thru 1-1/2	.003	.004	.005	.006	.005
Over 1-1/2 thru 2-1/2	.004	.005	.006	.007	.006
Over 2-1/2 thru 4	.005	.006	.007	.008	.007
Over 4 thru 6	.006	.007	.008	.009	---
Over 6 thru 8	.007	.008	.009	.010	---
Over 8 thru 9	.008	.009	.010	.011	---
<b>Hexagons</b>					
Up thru 3/4	.003	.004	.005	.007	---
Over 3/4 thru 1-1/2	.004	.005	.006	.008	---
Over 1-1/2 thru 2-1/2	.005	.006	.007	.009	---
Over 2-1/2 thru 3-1/8	.006	.007	.008	.010	---
Over 3-1/8 thru 4	.006	---	---	---	---
<b>Squares</b>					
Up thru 3/4	.003	.005	.006	.008	---
Over 3/4 thru 1-1/2	.004	.006	.007	.009	---
Over 1-1/2 thru 2-1/2	.005	.007	.008	.010	---
Over 2-1/2 thru 4	.007	.009	.010	.012	---
Over 4 thru 5	.011	---	---	---	---
<b>Flats (Width)</b>					
Up thru 3/4	.004	.005	.007	.009	---
Over 3/4 thru 1-1/2	.005	.006	.009	.011	---
Over 1-1/2 thru 3	.006	.007	.011	.013	---
Over 3 thru 4	.007	.009	.012	.017	---
Over 4 thru 6	.009	.011	.013	.021	---
Over 6	.014	---	---	---	---

Note: Tolerances for flats apply to thickness as well as to width.



# AISI A2 DCF

An air-hardening tool steel containing five percent chromium. Replaces the oil hardening (O1 type) when safer hardening, less distortion and increased wear-resistance are required. Provides an intermediate grade between the oil hardening and the high carbon, high chromium (D2) types.

## Typical Applications

Large Blanking Dies, Thread Roller Dies, Long Punches, Rolls, Master Hubs, Trimming Dies, Forming Dies, Precision Tools, Gauges, Coining Dies, Extrusion Dies, Mandrels, Shear Blades and Slitters.

Typical Analysis	Type A2 (UNS T30102)
Carbon (C)	0.95 / 1.05
Manganese (Mn)	1.00 max.
Silicon (Si)	0.50 max.
Tungsten (W)	
Molybdenum (Mo)	0.90 / 1.40
Chromium (Cr)	4.75 / 5.50
Vanadium (V)	0.15 / 0.50
*Nickel (Ni)	0.30 max.
<b>Forging (a)</b> Start forging at	1850 - 2000°F (1010 - 1093°C)
Do not forge below	1650°F (899°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature	1550 - 1600°F (843 - 871°C)
Rate of cooling, max. per hour	40°F (22°C)
Typical annealed hardness, Brinell	201 - 235
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly 1450 °F (788°C) 1700 - 1800°F (927 - 962°C) 20 - 45 (j) A (l)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	350 - 1000°F (177 - 538°C) 57 - 62
<b>Wear Resistance</b>	High
<b>Toughness</b>	Medium
<b>Resistance to Softening Effect of Elevated Temperature</b>	Medium to High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	Medium
<b>Distortion in Heat Treating</b>	Lowest
<b>Safety in Hardening</b>	Highest
<b>Resistance to Decarburization</b>	Medium

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI A6

A6 is an air-hardening, non-deforming tool steel that combines the deep hardening characteristics of air-hardening steels with the simplicity of low temperature heat treatment possible in many of the oil-hardening grades.

## Typical Applications

Blanking Dies, Precision Tools, Forming Dies, Coining Dies, Master Hubs, Shear Blades, Plastic Molds, Spindles, Mandrels, Heavy Duty Punches.

Typical Analysis	Type A6 (UNS T30106)
Carbon (C)	0.65 / 0.75
Manganese (Mn)	1.80 / 2.50
Silicon (Si)	0.50 max.
Tungsten (W)	
Molybdenum (Mo)	0.90 / 1.40
Chromium (Cr)	0.90 / 1.20
Vanadium (V)	
Cobalt (Co)	
*Nickel (Ni)	0.30 max.
<b>Forging (a)</b> Start forging at  Do not forge below	1900 - 2050°F (1038 - 1213°C) 1600°F (871°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1350 - 1375°F (732 - 746°C) 25°F (14°C) 217 - 248
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly 1200°F (649°C) 1525 - 1600°F (829 - 871°C) 20 - 45 (j) A (l)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	300 - 800°F (149 - 427°C) 54 - 60
<b>Wear Resistance</b>	Low to Medium
<b>Toughness</b>	Medium to High
<b>Resistance to Softening Effect of Elevated Temperature</b>	Medium
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Low to Medium
<b>Grindability</b>	Medium
<b>Distortion in Heat Treating</b>	Lowest
<b>Safety in Hardening</b>	Highest
<b>Resistance to Decarburization</b>	Medium to High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.



# AISI D2

D2 is an air-hardening, high carbon, high chromium tool steel with extremely high wear resisting properties. It is a very deep hardening steel and will be practically free from size change after proper treatment. The high percentage of chromium gives it mild corrosion-resisting properties in the hardened condition.

## Typical Applications

Blanking Dies, Forming Dies, Coining Dies, Slitting Cutters, Heading Tools, Long Punches, Forming Rolls, Edging Rolls, Master Tools, Beading Rolls, Intricate Punches, Extrusion Dies, Drawing Dies, Lamination Dies, Thread Rolling Dies, Shear Blades, Burnishing Tools, Gauges, Knurls, Wear Parts.

Typical Analysis	Type D2 (UNS T30402)
Carbon (C)	1.40 / 1.60
Manganese (Mn)	0.60 max.
Silicon (Si)	0.60 max.
Tungsten (W)	
Molybdenum (Mo)	0.70 / 1.20
Chromium (Cr)	11.00 / 13.00
Vanadium (V)	1.10 max.
Cobalt (Co)	1.00 max.
*Nickel (Ni)	0.30 max.
<b>Forging (a)</b> Start forging at	1850 - 2000°F (1010 - 1093°C)
Do not forge below	1700°F (927°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature	1600 - 1650°F (871 - 899°C)
Rate of cooling, max. per hour	40°F (22°C)
Typical annealed hardness, Brinell	217 - 255
<b>Hardening</b> Rate of heating	Very Slowly
Preheat temperature	1500°F (816°C)
Hardening temperature	1800 - 1875°F (982 - 1024°C)
Time at temperature, minutes	15 - 45 (j)
Quenching medium	A (l)
<b>Tempering</b> Tempering temperature	400 - 1000°F (204 - 538°C)
Approx. tempered hardness, Rockwell C	54 - 61
<b>Wear Resistance</b>	High to Very High
<b>Toughness</b>	Low
<b>Resistance to Softening Effect of Elevated Temperature</b>	Medium to High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Low
<b>Grindability</b>	Low
<b>Distortion in Heat Treating</b>	Lowest
<b>Safety in Hardening</b>	Highest
<b>Resistance to Decarburization</b>	Medium

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# DC53

DC53 is a general purpose, cold work die and mold steel whose strength and toughness approach those of high-speed steels.

## Typical Applications

Forming Dies, Thread Rolling Dies, Cold Forging Dies, Gauges, Plastic Molds, Stepped Punch and Press Punching Dies.

Typical Analysis	Type DC53
Carbon (C)	0.95
Molybdenum (Mo)	2.00
Chromium (Cr)	8.00
Vanadium (V)	0.25
Cobalt (Co)	
*Nickel (Ni)	
<b>Forging (a)</b> Start forging at Do not forge below	1100°C 900°C
<b>Normalizing (b)</b>	
<b>Annealing (c)</b> Temperature Rate of cooling, max. per hour Typical annealed hardness, Brinell	830°C - 880°C 40°F (22°C) 255°
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature Time at temperature, minutes Quenching medium	Slowly 800°C - 850°C) 1020° C - 1040°C 15 - 45 Air, Gas
<b>Tempering</b> Tempering temperature Approx. tempered hardness, Rockwell C	520 - 550°C 64 - 58
<b>Wear Resistance</b>	High to Very High
<b>Toughness</b>	High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Depth of Hardening</b>	Through Harden
<b>Machinability</b>	High
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	High
<b>Resistance to Decarburization</b>	High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI O1

O1 is an oil-hardening, non-deforming tool steel which can be hardened at relatively low temperatures. Tools and dies made from O1 will have good wearing qualities since the tungsten and higher chromium content gives improved wear resistance over the straight manganese grades.

## Typical Applications

Blanking Dies, Bushings, Forming Dies, Master Tools, Forming Rolls, Gauges, Trim Dies.

Typical Analysis	Type O1 (UNS T31501)
Carbon (C)	0.85 / 1.00
Manganese (Mn)	1.00 / 1.40
Silicon (Si)	0.50 max.
Tungsten (W)	0.40 / 0.60
Molybdenum (Mo)	
Chromium (Cr)	0.40 / 0.70
Vanadium (V)	0.30 max.
Cobalt (Co)	
*Nickel (Ni)	0.30 max.
<b>Forging (a)</b> Start forging at  Do not forge below	 1800 - 1950°F (982 - 1066°C)  1550°F (843°C)
<b>Normalizing (b)</b>	1600°F (871 °C)
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	 1400 - 1450°F (760 - 788°C)  40°F (22°C) 183 - 212
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	 Slowly 1200°F (649°C) 1450 - 1500°F (788 - 816°C)  10 - 30 0 (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	 350 - 500°F (177 - 260°C)  57 - 62
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Medium
<b>Resistance to Softening Effect of Elevated Temperature</b>	Low
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	High
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	Medium to High
<b>Resistance to Decarburization</b>	High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI 06

O6 is an oil-hardening cold work steel which has outstanding machinability resulting from small particles of graphitic carbon uniformly distributed throughout the steel. These particles increase resistance to wear and galling in service. For an oil-hardening steel, O6 holds size well during heat treating.

## Typical Applications

Blanking Dies, Piercing Dies, Drawing Dies, Pneumatic Hammers, Forming Dies, Spinning Tools, Punches, Stamps, Gauges, Wear Plates, Cams, Rotary Slitting Cutters.

Typical Analysis	Type O6 (UNS T31506)
Carbon (C)	1.25 / 1.55
Manganese (Mn)	0.30 / 1.10
Silicon (Si)	0.55 / 1.50
Tungsten (W)	
Molybdenum (Mo)	0.20 / 0.30
Chromium (Cr)	0.30 max
*Nickel (Ni)	0.30 max
<b>Forging (a)</b> Start forging at  Do not forge below	1800 - 1950°F (982 - 1066°C) 1500°F (816°C)
<b>Normalizing (b)</b>	1600°F (871 °C)
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1400 - 1450°F (766 - 788°C) 20°F (11°C) 183 - 217
<b>Hardening</b> Rate of heating Preheat Temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly  1450 - 1500°F (788 - 816°C) 10 - 30 0 (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	350 - 600°F (177 - 316°C) 58 - 63
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Medium
<b>Resistance to Softening Effect of Elevated Temperature</b>	Low
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	Highest
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	Medium to High
<b>Resistance to Decarburization</b>	High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.



# AISI L6

L6 is a tough, oil-hardening tool steel possessing a fine-grained structure and desirable shock resistance. L6 is also associated with high strength and good non-deforming characteristics.

## Typical Applications

Forming Rolls, Spindles, Punches, Trim Dies, Blanking Dies, Embossing Dies, Forming Dies, and Shear Blades.

Typical Analysis	Type L6 (UNS T61206)
Carbon (C)	0.65 / 0.75
Manganese (Mn)	0.25 / 0.80
Silicon (Si)	0.50 max
Molybdenum (Mo)	0.50 max
Chromium (Cr)	0.60 / 1.20
Vanadium (V)	0.30 max
*Nickel (Ni)	1.25 / 2.00
<b>Forging (a)</b> Start forging at  Do not forge below	1800 - 2000°F (982 - 1093°C)  1550°F (843°C)
<b>Normalizing (b)</b>	1600°F (871 °C)
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1400 - 1450°F (760 - 788°C) 40°F (22°C) 183-255
<b>Hardening</b> Rate of heating Hardening temperature  Time at temperature, minutes Quenching medium	Slowly 1450 - 1550°F (788 - 843°C) 10 - 30 (j) 0 (l)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	350 - 1000°F (177 - 538°C) 45 - 62
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	Low
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	Medium
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	Medium
<b>Resistance to Decarburization</b>	High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI S5

S5 is an oil-hardening silicon-manganese steel of medium carbon content especially adapted for punches, shear blades, chisels, and other shock resisting applications. S5 is therefore applicable where the properties of silicon-manganese steels are desired in combination with well-known advantages of oil-hardening steels. A reduced tendency to distort or crack in heat treatment is accordingly combined with high toughness in S5.

Typical Analysis	Type S5 (UNS T41905)
Carbon (C)	0.50 / 0.65
Manganese (Mn)	0.60 / 1.00
Silicon (Si)	1.75 / 2.25
Tungsten (W)	
Molybdenum (Mo)	0.20 / 1.35
Chromium (Cr)	0.35 max
Vanadium (V)	0.35 max
Cobalt (Co)	
<b>Forging (a)</b> Start forging at  Do not forge below	1850 - 2050°F (1010 - 1121°C) 1600°F (871°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1425 -1475°F (774 - 802°C) 25°F (14°C) 192-229
<b>Hardening</b> Rate of heating Preheat Temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly 1400°F (760°C) 1600 - 1700°F (871 - 927°C) 5 - 20 0 (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	350 - 800°F (177 - 427°C) 50 - 60
<b>Wear Resistance</b>	Low to Medium
<b>Toughness</b>	Highest
<b>Resistance to Softening Effect of Elevated Temperature</b>	Low
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	Medium to High
<b>Grindability</b>	Medium to High
<b>Distortion in Heat Treating</b>	Medium
<b>Safety in Hardening</b>	High
<b>Resistance to Decarburization</b>	Low

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI S7

AISI S7 is a general purpose air-hardening tool steel with high impact and shock resistance. It has good resistance to softening at moderately high temperatures. This combination of properties makes it suitable for many hot work and cold work applications. Excellent combination of high strength and toughness. Useful in moderate hot work as well as cold work tooling. Added size stability when air hardened.

## Typical Applications

Bull Riveters, Concrete Breakers (Moll Points), Riveting Dies, Powder Metal Dies, Notching Dies, Dowels, Drills, Drill Plates, Hubs, Plastic Mold Dies, Cold Forming Dies, Blanking Dies, Bending Dies, and Master Hobs.

Typical Analysis	Type S7 (UNS T41907)
Carbon (C)	0.45 / 0.55
Manganese (Mn)	0.20 / 0.80
Silicon (Si)	0.20 / 1.00
Tungsten (W)	
Molybdenum (Mo)	1.30 / 1.80
Chromium (Cr)	3.00 / 3.50
Vanadium (V)	0.30 max
Cobalt (Co)	
<b>Forging (a)</b> Start forging at  Do not forge below	1950 - 2050°F (1066 - 1121°C) 1700°F (927°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (C)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1500 - 1550°F (816 - 843°C) 25°F (14°C) 187-223
<b>Hardening</b> Rate of heating Preheat Temperature  Hardening temperature  Time at temperature, minutes Quenching medium	Slowly 1200 - 1300°F (649 - 704°C) 1700 - 1750°F (927 - 954°C) 15 - 45 (j) A or O (l)
<b>Tempering</b> Tempering temperature (Do not temper below 400°F) Approx. tempered hardness, Rockwell C	400 - 1150°F (204 - 621°C) 45 - 57
<b>Wear Resistance</b>	Low to Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Depth of Hardening</b>	Medium to Deep
<b>Machinability</b>	Medium to High
<b>Grindability</b>	Medium to High
<b>Distortion in Heat Treating</b>	A: Lowest /O: Low
<b>Safety in Hardening</b>	A: Highest /O: High
<b>Resistance to Decarburization</b>	Medium

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI S7 ESR

S7 ESR tool steel is specifically designed for use in molds and other applications where a highly polished or a very smooth finish is required. The ESR (Electro Slag Remelt) process removes most of the non-metallic inclusions in the steel. S7 ESR double melt's relatively low carbon level, fortified chemistry, ultra-clean, uniform, and homogeneous internal structure make it superior to the other conventionally manufactured shock-resisting tool steels. The following charts show microcleanliness ratings of ESR tool steels by ASTM E45, Method D:

Typical Microcleanliness	A	B	C	D
Thin	< 0.5	< 0.5	< 0.5	1.0
Heavy	< 0.5	< 0.5	< 0.5	1.0

Maximum Rated Microcleanliness	A	B	C	D
Thin	1.5	1.5	2.0	1.5
Heavy	1.0	1.0	1.0	1.0

The quality control of the S7 ESR process assures the exceptional cleanliness throughout by removing most harmful inclusions in the material (such as, oxides, nitrides and sulfides). The ESR steel produced will reflect a mirror like surface condition, subsequently reducing friction giving you easier ejection of parts, the elimination of minute scratches, and other stress-raisers that could lead to premature die failures.

The higher quality steel produced by special melt practices imparts a most important characteristic—freedom of inclusions and other imperfections. Other advantages include: cleanliness, stability, improved mechanical properties, structures relatively free from segregation resulting in less cracking, and quality assurance by ultrasonic testing of all ESR material produced.

Typical Analysis	Type S7 ESR
Carbon (C)	.50
Manganese (Mn)	.60
Silicon (Si)	.65
Molybdenum (Mo)	1.40
Chromium (Cr)	3.25
<b>Annealing (C)</b> When properly annealed, this steel has a machinability rating of 95 as compared to a 1% carbon steel rated at 100.	
<b>Tempering</b>	
Tempering	Rockwell C
As Quenched .....	60
400°F .....	58
500°F .....	56
600°F .....	55
700°F .....	54
800°F .....	53
900°F .....	52
1000°F .....	51
1100°F .....	47
1200°F .....	38
1" specimen, 3 long were air-hardened from 1725°F.	
Material may become brittle when tempered at less than 400°F.	

Please refer to pg. 8-58 for Hardening information  
\* Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.



# AISI P20

## Prehardened

P20 is a chrome-moly tool steel made specifically to fill the requirements for the machined cavities and forces used in zinc die casting and plastic molding. It is delivered fully quenched and tempered to approximately Brinell 300. Other hardness levels may be obtained through additional heat treatment. P20 composition and structure provide excellent machining and polishing characteristics.

Typical Analysis	Type P20 (UNS T51620)
Carbon (C)	0.35
Manganese (Mn)	0.80
Silicon (Si)	0.50
Tungsten (W)	
Molybdenum (Mo)	0.45
Chromium (Cr)	1.70
Vanadium (V)	
Cobalt (Co)	
Nickel (Ni)	
<b>Forging (a)</b> Start forging at Do not forge below	2000°F (1093°C) 1700°F (927°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1450-1500°F (788-816°C) 30°F per hour to 1000°F 207 max.
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly None 1500-1600°F (816-871°C) 60 min. per inch of thick. O (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	300-1200°F (149-649°C) 26-54
<b>Wear Resistance</b>	Low to Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Depth of Hardening</b>	Medium to Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	Medium
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	High
<b>Resistance to Decarburization</b>	High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI T420 Stainless ESR

AISI T420 ESR is an air or oil hardening mold steel having superior internal steel cleanliness combined with good resistance to corrosion. It is suitable for mold applications and is capable of providing an excellent polished surface. A special re-melting process called Electro Slag Refining or ESR provides a 420 type steel with the very low inclusion content required by mold makers who polish mold surfaces.

Typical Analysis	Type T420 (UNS S42000)
Carbon (C)	Over 0.15
Manganese (Mn)	1.00 max
Silicon (Si)	1.00 max
Tungsten (W)	0.03 max
Molybdenum (Mo)	0.03 max
Chromium (Cr)	12.00 / 14.00
Vanadium (V)	
Cobalt (Co)	
*Nickel (Ni)	
<b>Forging (a)</b> Start forging at  Do not forge below	
<b>Normalizing (b)</b>	
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1600 - 1650°F (871 - 899°C)  192 - 241
<b>Hardening</b> Rate of heating Preheat temperature  Hardening temperature  Time at temperature, minutes Quenching medium	1350 - 1450°F (735 - 788°C) 1850 - 1950°F (1110 - 1066°C)  A (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	450 - 750°F (232 - 399°C) 49 - 53
<b>Wear Resistance</b>	Low
<b>Toughness</b>	Medium
<b>Resistance to Softening Effect of Elevated Temperature</b>	Good
<b>Depth of Hardening</b>	Medium
<b>Machinability</b>	Medium
<b>Grindability</b>	Good
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	High
<b>Resistance to Decarburization</b>	Medium

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.  
\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI W2

W2 is a shallow hardening tool steel. Due to its vanadium content, the grain is superior in toughness and resistance to fatigue compared to straight carbon tool steels thereby making it desirable for many types of impact tools.

Typical Analysis	Type W2 (UNS T27302)
Carbon (C)	0.85 / 1.50
Manganese (Mn)	0.10 / 0.40
Silicon (Si)	0.10 / 0.40
Tungsten (W)	0.15 max
Molybdenum (Mo)	0.10 max
Chromium (Cr)	0.15 max
Vanadium (V)	0.15 / 0.35
Cobalt (Co)	
*Nickel (Ni)	0.20 max
<b>Forging (a)</b> Start forging at  Do not forge below	1800 - 1950°F (982 - 1066°C) 1500°F (816°C)
<b>Normalizing (b)</b>	1450 - 1700°F (d)
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1360 - 1450°F(d) (738 - 788°C) 40°F (22°C) 156 - 201
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	Slowly (g) 1400 - 1550°F (e) (760 - 843°C) 10 - 30 B or W (l)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	350 - 650°F (177 - 343°C) 50 - 64
<b>Wear Resistance</b>	Low to Medium
<b>Toughness</b>	High (l)
<b>Resistance to Softening Effect of Elevated Temperature</b>	Low
<b>Depth of Hardening</b>	Shallow
<b>Machinability</b>	Highest
<b>Grindability</b>	Highest
<b>Distortion in Heat Treating</b>	High
<b>Safety in Hardening</b>	Low to Medium
<b>Resistance to Decarburization</b>	Highest

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.

\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.

# AISI H13

H13 is a 5% chromium hot work tool steel designed for applications that require extreme toughness combined with good red-hardness. H13 will allow an extra margin of safety in tools subject to heavy hammer blows, and those containing deep recesses or sharp corners. Although H13 was designed as a hot work steel, it has solved many cold work applications where extra toughness could be gained with some sacrifice of wear resistance.

## Typical Applications

Aluminum Extrusion Dies, Die Casting Dies, Heavy Duty Compression Tools, Forming Punches, Hot Forging Dies, Shear Blades, Plastic Mold Dies, and Bolt Dies.

Typical Analysis	Type H13 (UNS T20813)
Carbon (C)	0.32 / 0.45
Manganese (Mn)	0.20 / 0.50
Silicon (Si)	0.80 / 1.20
Tungsten (W)	
Molybdenum (Mo)	1.10 / 1.75
Chromium (Cr)	4.75 / 5.50
Vanadium (V)	0.80 / 1.20
Cobalt (Co)	
*Nickel (Ni)	0.30 max
<b>Forging (a)</b> Start forging at  Do not forge below	1950 - 2100°F (1066 - 1149°C) 1650°F (899°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1550 - 1650°F (843 - 899°C) 40°F (22°C) 192 - 229
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes Quenching medium	Moderately from preheat 1500°F (816°C) 1825 - 1900°F (996 - 1038°C) 15 - 40 (j) A (l)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	1000-1200°F (k) (538-649°C) 38-53
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium to High
<b>Grindability</b>	Medium to High
<b>Distortion in Heat Treating</b>	Very Low
<b>Safety in Hardening</b>	Highest
<b>Resistance to Decarburization</b>	Medium to High

Please refer to pg. 8-58 for notes (a) to (o) incl., explanation of letter O, A, S, B and W.  
\*Unless otherwise specified, nickel plus copper equal 0.75% max. for all tool steel types.





# Viscount 44®

## Prehardened AISI Type H13 Typical Analysis

Viscount 44® is fully heat treated H13 hot work steel with carefully controlled and evenly dispersed sulphide additives. It is the same analysis type as Latrobe's popular VDC, but the free-machining sulphides improve the machinability to the point where die work at a hardness of Rockwell C 42-46 is practical. It is thus possible to bypass the risk of heat treatment involved in tool building.

Prehardening gives Viscount 44® a tremendous advantage when used for hot work dies because of the constant danger of size change or distortion during heat treatment. The product also eliminates costly finishing operations after heat treatment.

Using prehardened Viscount 44® for extrusion tools makes it possible to produce dies, backers, bolsters, dummy blocks, etc. in a few hours, allowing extremely short delivery schedules to be met. In addition, the use of prehardened Viscount 44® for extrusion dies ensures clean metal at the bearing surfaces free from any possible decarburization, carburization, scale, sub-scale or other deleterious conditions sometimes encountered when finished dies are heat treated.

Field tests show that Viscount 44®'s performance in aluminum, magnesium, and zinc die casting dies is at best the equivalent of regular H13. Particular examples have shown that over 100,000 shots can be obtained in large dies and over 200,000 shots in smaller dies.

Field reports also indicate excellent performance with Viscount 44® on forging dies, plastic molds, extrusion tools, and other hot work tools.

Typical Analysis	Viscount 44®
Carbon (C)	0.40
Manganese (Mn)	0.80
Silicon (Si)	1.00
Tungsten (W)	
Molybdenum (Mo)	1.35
Chromium (Cr)	5.25
Vanadium (V)	1.00
Cobalt (Co)	
<b>Tempering</b> Approx. tempered hardness, Rockwell C	42 - 46
<b>Wear Resistance</b>	Medium
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Depth of Hardening</b>	
<b>Machinability</b>	Low
<b>Grindability</b>	Medium
<b>Distortion in Heat Treating</b>	
<b>Safety in Hardening</b>	
<b>Resistance to Decarburization</b>	

# DRM1

## Hot and Warm Forging Die Steel

DRM1 tool steel features high hardness and high tough Matrix type high speed tool steel vastly surpasses hot work die steels. DRM1 improves hot and warm die life by its higher toughness than conventional grade.

### Typical Applications

Used for hot and warm forging dies and punches.

Typical Analysis	Type DRM1
Carbon (C)	0.60
Manganese (Mn)	0.50
Silicon (Si)	0.20
Tungsten (W)	3.00
Molybdenum (Mo)	1.00
Chromium (Cr)	4.20
Vanadium (V)	1.50
Cobalt (Co)	2.00
<b>Annealing (c)</b> Temperature	1472 - 1616°F (800 - 880°C)
Slow cooling	
Typical annealed hardness, Brinell	≤ 235HB
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes  Quenching	Moderately from preheat 1742°F (950°C) 2012 - 2084°F (1100 - 1140°C)  20-30 per inch of thickness for material under 4" 10-20 per inch of thickness for material 4" and over OQ-Oil Quenching, GC-Gas Quenching in vacuum furnace, Salt Bath, Similar to conventional high speed steels
<b>Tempering</b>  Tempering temperature  Approx. tempered hardness, Rockwell C	Minimal Double Temper AC-Air Cooling, 1022-1148°F (550-620°C) 56-58 HRC
<b>Wear Resistance</b>	Good
<b>Toughness</b>	Very High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Machinability</b>	Better and faster than conventional high speed steels
<b>Grindability</b>	Better and faster than conventional high speed steels

# DRM2

## Warm and Cold Forging Die Steel

DRM2 is a matrix type high speed tool steel available for warm and cold forging tools where critical performance is required. DRM2 prolongs service life due to its higher hardness and toughness than those of conventional grades.

### Typical Applications

Used for warm and cold forging dies and punches.

Typical Analysis	Type DRM2
Carbon (C)	0.70
Tungsten (W)	1.00
Molybdenum (Mo)	2.40
Chromium (Cr)	5.50
Vanadium (V)	1.00
<b>Annealing (c)</b> Temperature  Slow cooling Typical annealed hardness, Brinell	1472 - 1616°F (800 - 880°C)  ≤ 235HB
<b>Hardening</b> Rate of heating Preheat temperature Hardening temperature  Time at temperature, minutes  Quenching	Moderately from preheat 1742°F (950°C) 1922 - 2012°F (1050 - 1100°C)  20-30 per inch of thickness for material under 4" 10-20 per inch of thickness for material 4" and over  OQ-Oil Quenching, GC-Gas Quenching in vacuum furnace, Salt Bath, Similar to conventional high speed steels
<b>Tempering</b>  Tempering temperature  Approx. tempered hardness, Rockwell C	Minimal Double Temper AC-Air Cooling, 1022 - 1148°F (550 - 620°C)  58 - 62 HRC
<b>Wear Resistance</b>	Good
<b>Toughness</b>	High
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Machinability</b>	Better and faster than conventional high speed steels
<b>Grindability</b>	Better and faster than conventional high speed steels

# DRM3

## Cold Forging Die Steel

Conventional grade MH88 has been improved to DRM3. High hardness and tough DRM3 with excellent hardenability is suitable for high precision cold working tools.

### Typical Applications

Used for hot and warm forging dies and punches.

Typical Analysis	Type DRM3
Carbon (C)	0.80
Manganese (Mn)	0.35
Silicon (Si)	0.70
Tungsten (W)	0.95
Molybdenum (Mo)	4.35
Chromium (Cr)	5.50
Vanadium (V)	1.20
<b>Annealing (c)</b>	
Temperature	1472 - 1616°F (800 - 880°C)
Slow cooling	
Typical annealed hardness, Brinell	≤ 235HB
<b>Hardening</b>	
Rate of heating	Moderately from preheat
Preheat Temperature	1742°F (950°C)
Hardening temperature	2012 - 2084°F (1100 - 1140°C)
Time at temperature, minutes	30 - 90
Quenching	OQ-Oil Quenching, GC-Gas Quenching in vacuum furnace, Salt Bath, Similar to conventional high speed steels
<b>Tempering</b>	Minimal Double Temper AC-Air Cooling,
Tempering temperature	1022-1148°F (550-620°C)
Approx. tempered hardness, Rockwell C	62-66 HRC
<b>Wear Resistance</b>	Very High
<b>Toughness</b>	Good
<b>Resistance to Softening Effect of Elevated Temperature</b>	High
<b>Machinability</b>	Better and faster than conventional high speed steels
<b>Grindability</b>	Better and faster than conventional high speed steels

# AISI M2

M2 is a tungsten-molybdenum high-speed steel and is a popular grade for general purpose cutting and non-cutting applications. It has a wider heat-treating range than most of the molybdenum high-speed steels, coupled with a resistance to decarburization that is characteristic of tungsten types. M2 offers an excellent combination of red hardness, toughness, and wear resistance. M2 is available in a wide variety of shapes and sizes. As with all Alro Specialty Metal products, M2 is subjected to a variety of rigid quality control tests and inspection to ensure quality, uniformity, and reliability.

## Typical Applications

Broaches, Boring Tools, Chasers, Cold Forming Rolls, Cold Heading Inserts, Drills, End Mills, Form Tools, Hobs, Lathe and Planer Tools, Punches, Milling Cutters, Taps, Reamers, and Saws.

Typical Analysis	Type M2 (UNS T11302)
Carbon (C)	0.78 / 0.88
Manganese (Mn)	0.15 / 0.88
Silicon (Si)	0.20 / 0.45
Tungsten (W)	5.50 / 6.75
Molybdenum (Mo)	4.50 / 5.50
Chromium (Cr)	3.75 / 4.50
Vanadium (V)	1.75 / 2.20
Nickel (Ni)	0.30 max
<b>Forging (a)</b> Start forging at  Do not forge below	1900 - 2100°F (1038 - 1149°C)  1700°F (927°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1600 - 1650°F (871 - 899°C) 40°F (22°C) 212 - 241
<b>Hardening</b> Rate of heating Preheat Temperature Hardening temperature  Time at temperature, minutes Quenching medium	Rapidly from preheat 1350-1550°F (732-843°C) 2175-2250°F (h) (1191-1232°C) 2-5 O, A, or S (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	1000-1100°F (538-593°C) 60-65
<b>Wear Resistance</b>	Very High
<b>Toughness</b>	Low
<b>Resistance to Softening Effect of Elevated Temperature</b>	Very High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	Low
<b>Distortion in Heat Treating</b>	A or S: Low/O: Medium
<b>Safety in Hardening</b>	Medium
<b>Resistance to Decarburization</b>	High

# AISI M3

M3 was developed after extensive studies of the effect of increased carbon and vanadium contents on the intermediate molybdenum-tungsten high-speed steels. The analysis was tried and proven on practically all high-speed steel applications. M3 offers the unusual combination of extremely high-edge strength at high hardness levels. With few exceptions, best life is accomplished with a minimum hardness of 65.5 Rockwell C. Experience indicates that the chemical balance achieved in M3 results in optimum combination of cutting ability, abrasion resistance, edge strength, red hardness, and long service life. M3 is more readily machined and offers less grinding resistance than higher vanadium types.

## Typical Applications

Drills, Taps, End Mills, Reamers, Counterbores, Broaches, Hobs, Form Tools, Lathe and Planer Tools, Checking Tools, Milling Cutters, Slitting Saws, Punches, Drawing Dies, and Wood Working Knives.

Typical Analysis	Type M3 (UNS T11313)
Carbon (C)	1.00 - 1.10
Manganese (Mn)	0.15 - 0.40
Silicon (Si)	0.20 - 0.45
Tungsten (W)	5.00 - 6.75
Molybdenum (Mo)	4.75 - 6.50
Chromium (Cr)	3.75 - 4.50
Vanadium (V)	2.25 - 2.75
Nickel (Ni)	0.30 max
<b>Forging (a)</b> Start forging at  Do not forge below	1900 - 2100°F (1038 - 1149°C) 1700°F (927°C)
<b>Normalizing (b)</b>	Do not normalize
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1600 - 1650°F (871 - 899°C) 40°F (22°C) 223 - 255
<b>Hardening</b> Rate of heating Preheat Temperature Hardening temperature  Time at temperature, minutes Quenching medium	Rapidly from preheat 1350 - 1550°F (732-843°C) 2200 - 2250°F (h) (1191 - 1232°C) 2 - 5 O, A, or S (l)
<b>Tempering</b> Tempering temperature Approx. tempered hardness, Rockwell C	1000-1100°F (538-593°C) 61 - 66
<b>Wear Resistance</b>	Highest
<b>Toughness</b>	Low
<b>Resistance to Softening Effect of Elevated Temperature</b>	Very High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	Very Low
<b>Distortion in Heat Treating</b>	A or S: Low/O: Medium
<b>Safety in Hardening</b>	Medium
<b>Resistance to Decarburization</b>	High

# AISI M4 (PM)

M4 PM, a member of the molybdenum-tungsten family of high-speed steels, is a special purpose grade which utilizes its higher carbon and vanadium contents to develop excellent abrasion resistance. Produced conventionally, M4 is difficult to machine in the annealed condition and grind in the hardened condition. M4 PM is produced by the powder metallurgy process and allows an addition of .06/.08 sulfur which provides a uniform dispersion of small sulfides throughout the structure and enhances machinability. Coupled with finer carbides and structural uniformity, better grindability is also achieved. These factors, along with increased toughness, are ideally suited for heavy-duty cold-work applications.

## Typical Applications

Blades, Broaches, Chasers, Die Inserts, Form Tools, Lathe and Planer Tools, Milling Cutters, Punches, Reamers, Slitter Knives, Spade Drills, and Taps.

Typical Analysis	Type M4 PM (UNS T11304)
Carbon (C)	1.30
Manganese (Mn)	0.30
Silicon (Si)	0.40
Tungsten (W)	5.50
Molybdenum (Mo)	4.50
Chromium (Cr)	4.50
Vanadium (V)	4.00
Sulphur (S)	0.07
<b>Forging (a)</b> Start forging at Do not forge below	
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1550 - 1600°F (843 - 871°C)
<b>Hardening</b> Rate of heating Preheat Temperature  Hardening temperature  Time at temperature, minutes Quenching medium	1450 - 1550°F (788 - 843°C) 2150 - 2250°F (h) (1176 - 1232°C) 10 - 30 O (I)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	1000 - 1100°F (538 - 593°C) 62 - 66
<b>Wear Resistance</b>	Highest
<b>Toughness</b>	Low
<b>Resistance to Softening Effect of Elevated Temperature</b>	Very High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Low
<b>Safety in Hardening</b>	Medium
<b>Resistance to Decarburization</b>	Medium

# AISI M42

M42 is a molybdenum-cobalt high-speed steel capable of being hardened to 70 Rockwell C. The carbon content is higher than in most high-speed steels, and with this balanced composition, contributes to wear resistance and hot hardness as well as the high hardness capability. M42 exhibits good grindability and relatively good toughness at high hardness levels. M42 is being used for the machining of heat treated materials (high hardness) and high temperature alloys.

## Typical Applications

Broaches, Circular and Dovetail Form Tools, Drills, End Mills, Lathe Tools, Milling Cutters, Punches, Reamers, Slitting Saws, and Twist Drills.

Typical Analysis	Type M42 (UNS T11342)
Carbon (C)	1.05 - 1.15
Manganese (Mn)	0.15 - 0.40
Silicon (Si)	0.15 - 0.65
Tungsten (W)	1.15 - 1.85
Molybdenum (Mo)	9.00 - 10.00
Chromium (Cr)	3.50 - 4.25
Vanadium (V)	0.95 - 1.35
Cobalt (Co)	7.75 - 8.75
Nickel (Ni)	0.30 max
<b>Forging (a)</b> Start forging at  Do not forge below	1900 - 2100°F (1038 - 1149°C)  1700°F (927°C)
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1600 - 1650°F (871 - 899°C) 40°F (22°C) 235 - 269
<b>Hardening</b> Rate of heating Preheat Temperature  Hardening temperature  Time at temperature, minutes Quenching medium	Rapidly from preheat 1350 - 1550°F (733 - 843°C) 2125 - 2175°F (h)(o) (1163 - 1191°C) 2 - 5 O, A, or S (l)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	950-1100°F (510-593°C)  65-70
<b>Wear Resistance</b>	Very High to Highest
<b>Toughness</b>	Low
<b>Resistance to Softening Effect of</b>	
<b>Elevated Temperature</b>	Highest
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	Low
<b>Distortion in Heat Treating</b>	A or S: Low/O: Medium
<b>Safety in Hardening</b>	Low to Medium
<b>Resistance to Decarburization</b>	Low



# AISI T15 (PM)

T15 PM is a tungsten high-speed steel designed for use in machining operations requiring heavy cuts, high speeds and feeds. Its primary use is in applications requiring the machining of high-hardness heat-treated materials such as high temperature alloys. The high carbon, vanadium, and cobalt contents contribute to good wear resistance, hot hardness and good hardness capabilities. T15 PM is produced by the powder metallurgy process which has resulted in improved quality from the standpoint of structural uniformity, response to heat treatment and grindability. These factors, along with increased toughness, are increased usage in the industry because of its recognized superior cutting ability.

## Typical Applications

Broaches, Chasers, Form Tools, Heavy Duty Cutting Tools, High Production Blades, Milling Cutters, Reamers, and Taps.

Typical Analysis	Type T15 PM (UNS T12015)
Carbon (C)	1.55
Manganese (Mn)	0.30
Silicon (Si)	0.30
Tungsten (W)	12.25
Molybdenum (Mo)	
Chromium (Cr)	4.00
Vanadium (V)	5.00
Cobalt (Co)	5.00
<b>Forging (a)</b> Start forging at  Do not forge below	
<b>Annealing (c)</b> Temperature  Rate of cooling, max. per hour Typical annealed hardness, Brinell	1600 - 1650°F (871 - 899°C)
<b>Hardening</b> Rate of heating Preheat Temperature  Hardening temperature  Time at temperature, minutes Quenching medium	1450 - 1500°F (788 - 816°C) 2175 - 2225°F (h)(o) (1190 - 1218°C)
<b>Tempering</b> Tempering temperature  Approx. tempered hardness, Rockwell C	1000 - 1100°F (538 - 593°C) 66 - 68
<b>Wear Resistance</b>	Highest
<b>Toughness</b>	Low
<b>Resistance to Softening Effect of Elevated Temperature</b>	Very High
<b>Depth of Hardening</b>	Deep
<b>Machinability</b>	Medium
<b>Grindability</b>	High
<b>Distortion in Heat Treating</b>	Medium
<b>Safety in Hardening</b>	Medium
<b>Resistance to Decarburization</b>	Medium

# Heat Treating Notes

- (a) The temperature at which to start heat treating is given as a range, the higher side of which should be used for large sections and heavy or rapid reductions, and the lower side for smaller sections and lighter reduction. As the alloy content of steel increases, the time of soaking at forging temperature increases proportionately. Likewise, as the alloy content increases, it becomes necessary to cool slowly from the maximum heating temperature. With very high alloy steels, such as high-speed steels and air-hardening steels, this slow cooling is imperative in order to prevent cracking and to leave the steel in semi-soft condition. Either furnace cooling or burying in an insulating medium, such as lime, mica, or silocel is satisfactory.
- (b) The length of time the steel is held after being uniformly heated through at the normalizing temperature varies from about 15 minutes for a small section to about one hour for large sizes. Cooling from the normalizing temperature is done in still air. The purpose of normalizing after forging is to refine the grain structure and to produce a uniform structure throughout the forging. Normalizing should not be confused with low temperature [about 1200°F (649°C)] annealing used for the relief of residual stresses resulting from heavy machining, bending, and forming.
- (c) The annealing temperature is given as a range, the upper limit of which should be used for large sections and the lower limit for smaller sections. The length of time the steel is held after being uniformly heated through at the annealing temperature varies from about one hour for light sections and small furnace charges of carbon or low alloy tool steel to about four hours for heavy sections and large furnace charges of high alloy steel.
- (d) Normalizing, annealing, and hardening temperatures of carbon tool steels are given as ranges as they vary with carbon content. The following temperatures are suggested:

## Normalizing

0.60 to 0.75%	C: 1500°F (816°C)
0.75 to 0.90%	C: 1450°F (788°C)
0.90 to 1.10%	C: 1600°F (871°C)
1.10 to 1.40%	C: 1600 to 1700°F (871 to 927°C)

## Annealing

0.60 to 0.90%	C: 1360 to 1400°F (738 to 760°C)
0.90 to 1.40%	C: 1400 to 1450°F (760 to 788°C)

- (e) Varies with carbon content as follows:
- |            |                               |
|------------|-------------------------------|
| 0.60-0.80% | C: 1450-1550°F (788 to 843°C) |
| 0.85-1.05% | C: 1425-1550°F (774 to 843°C) |
| 1.10-1.40% | C: 1400-1525°F (760 to 829°C) |
- (f) Toughness decreases with increasing carbon content and depth of hardening.
- (g) For large tools and tools having intricate sections, preheating at 1050-1200°F (566-649°C) is recommended.
- (h) When high temperature heating is carried out in a salt bath, the range of temperatures should be about 25°F (14°C) lower than that shown.
- (j) Times shown apply to open furnace heat treatment. For pack hardening a common rule is to heat for 1/2 hour per inch (25.4 mm) of cross section of the pack.
- (k) Double tempering suggested for not less than one hour at temperature each temper.
- (l) O: Oil quench  
A: Air Cool  
S: Salt bath quench  
B: Brine quench  
W: Water quench
- (m) Triple tempering suggested for not less than one hour at temperature each temper.
- (n) When high carbon material is involved, lowering of the hardening temperature an additional 25°F (14°C) is suggested. This is in addition to the 25°F (14°C) reduction involving salt bath hardening.
- (o) Available in two silicon contents, nominally 0.33% and 0.55%. When 0.55% silicon is used, the maximum suggested hardening temperature is 2150°F (1177°C).



# Tool Wrap

Tool Wrap is a revolutionary new approach to the heat treatment process. Here's how it works: wrap your parts in our special Tool Wrap as you would a package or a sandwich because Tool Wrap can be wrinkled, folded or cut with scissors (.002 thick T321 Stainless). Then place in your furnace and air cool as usual with the Tool Wrap on the material. Try Tool Wrap on all air hardening grades and hot work steels.

Consider the following advantages of Tool Wrap:

- ✓ No costly atmosphere or special controls needed.
- ✓ No time consuming Ni chrome box packing.
- ✓ Scale free heat treating.
- ✓ Hardened parts remain scale free, minimizing grinding.

Grade Availability		
Grade	Thickness	Maximum Temperature
321 Stainless	.002"	2000°F (1093°C)
309 Stainless	.002"	2240°F (1093°C)

*Tool Wrap edges are extremely sharp, gloves should always be worn when working with Tool Wrap.*

# Tool Steel Flats and Squares (DCF)

Size (inches)	Weight (lbs./foot)	Size (inches)	Weight (lbs./foot)	Size (inches)	Weight (lbs./foot)
3/8 x 1/2	0.785	1/2 x 1	1.924	5/8 x 5/8	1.553
3/4	1.126	1-1/8	2.148	3/4	1.829
1	1.466	1-1/4	2.371	7/8	2.106
1-1/4	1.806	1-3/8	2.594	1	2.382
1-3/8	1.977	1-1/2	2.818	1-1/8	2.659
1-1/2	2.147	1-3/4	3.264	1-1/4	2.935
1-3/4	2.487	1-7/8	3.488	1-3/8	3.212
2	2.827	2	3.711	1-1/2	3.488
2-1/4	3.168	2-1/4	4.158	1-3/4	4.041
2-1/2	3.508	2-1/2	4.604	2	4.594
2-3/4	3.848	2-3/4	5.051	2-1/4	5.148
3	4.189	3	5.498	2-1/2	5.701
3-1/2	4.869	3-1/4	5.944	2-3/4	6.254
3-3/4	5.210	3-1/2	6.391	3	6.807
4	5.550	4	7.284	3-1/4	7.360
4-1/2	6.231	4-1/2	8.178	3-1/2	7.913
5	6.911	5	9.071	4	9.019
6	8.272	5-1/2	9.964	4-1/2	10.125
6-1/2	8.953	6	10.858	5	11.231
7	9.634	6-1/2	11.751	5-1/2	12.337
8	10.995	7	12.644	6	13.443
9	12.356	8	14.431	6-1/2	14.549
10	13.718	9	16.218	7	15.655
12	18.691	10	18.004	8	17.867
1/2 x 1/2	1.031	12	23.849	9	20.079
5/8	1.254	14	27.783	10	22.291
3/4	1.478	16	31.717	12	29.006
7/8	1.701				



# Tool Steel Flats and Squares (DCF)

Alloys &  
Tool Steel

Alro Steel Metals Guide

Size (inches)	Weight (lbs./foot)
<b>3/4 x</b> 3/4	2.181
7/8	2.511
1	2.841
1-1/8	3.170
1-1/4	3.500
1-3/8	3.830
1-1/2	4.159
1-3/4	4.819
2	5.478
2-1/4	6.137
2-1/2	6.797
2-3/4	7.456
3	8.116
3-1/4	8.775
3-1/2	9.434
4	10.753
4-1/2	12.072
5	13.390
5-1/2	14.709
6	16.028
6-1/2	17.347
7	18.665
8	21.303
9	23.940
10	26.578
12	34.164
14	39.799
16	45.435
20	56.706
<b>7/8 x</b> 7/8	2.916
1	3.299
1-1/8	3.682
1-1/4	4.064
1-3/8	4.447
1-1/2	4.830
1-3/4	5.596
2	6.362
2-1/4	7.127
2-1/2	7.893
2-3/4	8.659
3	9.424
3-1/4	10.190
3-1/2	10.956
4	12.487
4-1/2	14.019
5	15.550
5-1/2	17.082
6	18.613

Size (inches)	Weight (lbs./foot)
<b>7/8 x</b> 7	21.676
8	24.739
9	27.802
10	30.865
12	39.321
<b>1 x</b> 1	3.757
1-1/4	4.629
1-3/8	5.065
1-1/2	5.501
1-3/4	6.373
2	7.245
2-1/4	8.117
2-1/2	8.989
2-3/4	9.861
3	10.733
3-1/2	12.478
4	14.222
4-1/2	15.966
5	17.710
5-1/2	19.454
6	21.198
6-1/2	22.942
7	24.687
8	28.175
9	31.663
10	35.151
12	44.479
14	51.816
16	59.153
<b>1-1/8 x</b> 1-1/8	4.704
1-1/4	5.193
1-1/2	6.172
1-3/4	7.150
2	8.129
2-1/4	9.107
2-1/2	10.086
2-3/4	11.064
3	12.042
3-1/2	13.999
4	15.956
4-1/2	17.913
5	19.870
<b>1-1/8 x</b> 5-1/2	21.827
6	23.783
8	31.611
10	39.438
12	49.636

Size (inches)	Weight (lbs./foot)
<b>1-1/4 x</b> 1-1/4	5.758
1-1/2	6.843
1-3/4	7.927
2	9.012
2-1/4	10.097
2-1/2	11.182
2-3/4	12.267
3	13.351
3-1/2	15.521
4	17.690
4-1/2	19.860
5	22.030
5-1/2	24.199
6	26.369
7	30.708
8	35.047
9	39.386
10	43.725
12	54.794
16	72.872
20	90.949
24	109.027
<b>1-3/8 x</b> 1-3/8	6.918
1-1/2	7.514
1-3/4	8.705
2	9.896
2-1/4	11.087
2-1/2	12.278
2-3/4	13.469
3	14.660
3-1/2	17.043
4	19.425
4-1/2	21.807
5	24.189
5-1/2	26.572
6	28.954
8	38.483
9	43.247
10	48.012
12	59.951
<b>1-1/2x</b> 1-1/2	8.184
1-3/4	9.482
2	10.779
2-1/4	12.077
2-1/2	13.374
2-3/4	14.672
3	15.969

## DCF Thickness and Width Oversize Ranges :

Width (based on thickness)	
Thru < 4" thick	+0.035 to +0.077 oversize
Rough Milled 4" thru < 5" ....	+0.062 to +0.124 oversize
Rough Milled 5" and over ....	+0.062 to +0.124 oversize

Thickness	
Thru < 4" thick	+0.015 to +0.035 oversize
Rough Milled 4" thru < 5" ....	+0.062 to +0.125 oversize
Rough Milled 5" and over ....	+0.125 to +0.250 oversize

**Note:** Actual weight may vary because of oversize tolerance. Sizes not listed above can be cut from plate.  
For Powdered Metal add 3% for weight.



# Tool Steel Flats and Squares (DCF)

Alloys &  
Tool Steel

Alro Steel Metals Guide

Size (inches)	Weight (lbs./foot)
<b>1-1/2x</b> 3-1/2	18.564
4	21.159
4-1/2	23.754
5	26.349
5-1/2	28.944
6	31.539
7	36.729
8	41.919
9	47.109
10	52.298
12	65.109
16	86.590
20	108.071
24	129.552
<b>1-3/4x</b> 1-3/4	11.036
2	12.546
2-1/4	14.057
2-1/2	15.567
2-3/4	17.077
3	18.587
3-1/2	21.608
4	24.628
4-1/2	27.648
5	30.669
5-1/2	33.689
6	36.709
7	42.750
8	48.791
9	54.831
10	60.872
12	75.424
<b>2 x</b> 2	14.314
2-1/4	16.036
2-1/2	17.759
2-3/4	19.482
3	21.205
3-1/2	24.651
4	28.097
4-1/2	31.542
5	34.988
5-1/2	38.434
6	41.880
7	48.771
8	55.662
9	62.554
10	69.445

Size (inches)	Weight (lbs./foot)
<b>2 x</b> 12	85.739
16	114.027
20	142.314
24	170.601
<b>2-1/4x</b> 2-1/4	18.016
2-1/2	19.952
2-3/4	21.887
3	23.823
3-1/2	27.694
4	31.565
4-1/2	35.436
5	39.308
5-1/2	43.179
6	47.050
7	54.792
8	62.534
9	70.277
10	78.019
12	96.054
<b>2-1/2x</b> 2-1/2	22.144
2-3/4	24.293
3	26.441
3-1/2	30.737
4	35.034
4-1/2	39.331
5	43.627
5-1/2	47.924
6	52.220
7	60.813
8	69.406
9	77.999
10	86.592
<b>2-1/2x</b> 12	106.369
16	141.463
20	176.557
24	211.651
<b>2-3/4x</b> 2-3/4	26.698
3	29.059
3-1/2	33.781
4	38.503
4-1/2	43.225
5	47.947
5-1/2	52.669
6	57.390
7	66.834
8	76.278
9	85.722

Size (inches)	Weight (lbs./foot)
<b>2-3/4x</b> 10	95.166
12	116.684
16	155.181
20	193.678
24	232.175
<b>3 x</b> 3	31.677
3-1/2	36.824
4	41.971
4-1/2	47.119
5	52.266
5-1/2	57.413
6	62.561
7	72.855
8	83.150
9	93.445
10	103.739
12	127.000
16	168.900
20	210.800
<b>3-1/2x</b> 3-1/2	42.911
4	48.909
4-1/2	54.907
5	60.905
5-1/2	66.903
6	72.901
7	84.898
8	96.894
9	108.890
10	120.887
12	147.630
16	196.336
20	245.043
<b>4 x</b> 4	55.846
4-1/2	62.695
5	69.544
5-1/2	76.393
6	83.242
7	96.940
8	110.638
9	124.336
10	138.034
12	168.260
16	223.773
20	279.286

## DCF Thickness and Width Oversize Ranges :

Width (based on thickness)	
Thru < 4" thick .....	+0.035 to +0.077 oversize
Rough Milled 4" thru < 5" .....	+0.062 to +0.124 oversize
Rough Milled 5" and over ....	+0.062 to +0.124 oversize

Thickness	
Thru < 4" thick .....	+0.015 to +0.035 oversize
Rough Milled 4" thru < 5" .....	+0.062 to +0.125 oversize
Rough Milled 5" and over ....	+0.125 to +0.250 oversize

**Note:** Actual weight may vary because of oversize tolerance. Sizes not listed above can be cut from plate.

For Powdered Metal add 3% for weight.

# Tool Steel Flats and Squares (DCF)

Size (inches)	Weight (lbs./foot)
4-1/2 x 4-1/2	72.041
5	79.831
6	95.411
8	126.571
10	157.730

Size (inches)	Weight (lbs./foot)
5 x 5	88.550
5-1/2	97.191
6	105.832
7	123.113
8	140.394
10	174.957
12	209.520
5-1/2x 5-1/2	106.761
6	116.252
8	154.218
10	192.184

Size (inches)	Weight (lbs./foot)
6 x 6	126.673
7	147.357
8	168.042
10	209.411
12	250.781

\* 10" thick plate is available in some grades. Please inquire.

## DCF Thickness and Width Oversize Ranges :

Width (based on thickness)	
Thru < 4" thick	+0.035 to +0.077 oversize
Rough Milled 4" thru < 5" ....	+0.062 to +0.124 oversize
Rough Milled 5" and over ....	+0.062 to +0.124 oversize

Thickness	
Thru < 4" thick	+0.015 to +0.035 oversize
Rough Milled 4" thru < 5" ....	+0.062 to +0.125 oversize
Rough Milled 5" and over ....	+0.125 to +0.250 oversize

**Note:** Actual weight may vary because of oversize tolerance. Sizes not listed above can be cut from plate.  
For Powdered Metal add 3% for weight.

# Carbon and Alloy Plate Tolerances

Tolerance Over Specified Thickness for Widths Given (inches)								
Specified Thickness (inches)	Up thru 48"	>48" up to 60"	>60" up to 72"	>72" up to 84"	>84" up to 96"	>96" up to 108"	>108" up to 120"	>120" up to 132"
Up thru 1/4	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
>1/4 to 5/16	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.04
5/16 to 3/8	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.04
3/8 to 7/16	0.03	0.03	0.03	0.03	0.03	0.03	0.04	0.04
7/16 to 1/2	0.03	0.03	0.03	0.03	0.03	0.03	0.04	0.04
1/2 to 5/8	0.03	0.03	0.03	0.03	0.03	0.03	0.04	0.04
5/8 to 3/4	0.03	0.03	0.03	0.03	0.03	0.04	0.04	0.04
3/4 to 1	0.03	0.03	0.03	0.03	0.04	0.04	0.05	0.05
1 to 2	0.06	0.06	0.06	0.06	0.06	0.07	0.08	0.10
2 to 3	0.09	0.09	0.09	0.10	0.10	0.11	0.12	0.13
3 to 4	0.11	0.11	0.11	0.11	0.11	0.13	0.14	0.14
4 to 6	0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.15
6 to 10	0.23	0.24	0.24	0.24	0.24	0.24	0.24	0.24
10 to 12	0.29	0.29	0.33	0.33	0.33	0.33	0.33	0.33
12 to 15	0.29	0.29	0.35	0.35	0.35	0.35	0.35	0.35

Permissible variations in thickness for rectangular carbon, high strength, low alloy and alloy-steel plates, when ordered to thickness.

Note<sup>1</sup>: Permissible variation under specified thickness - 0.01"

Note<sup>2</sup>: Thickness to be measured at 3/8" to 3/4" from longitudinal edge.

Note<sup>3</sup>: For thickness measured at any location other than that specified in Note<sup>2</sup>, the permissible maximum over tolerance shall be increased by 75%, rounded to the nearest 0.01".



# Tool Steel Rounds (DCF)

Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)	Diameter (inches)	Weight (lbs./foot)
1/4	.182	2-3/4	20.817	8-1/2	204.154
5/16	.285	2-7/8	22.725	8-3/4	211.460
3/8	.404	3	25.778	9	228.202
7/16	.545	3-1/8	27.896	9-1/2	253.589
1/2	.727	3-1/4	30.099	10	280.423
9/16	.912	3-1/2	34.754	10-1/2	308.492
5/8	1.117	3-3/4	39.745	11	337.900
11/16	1.344	4	45.070	11-1/2	368.646
3/4	1.591	4-1/4	51.079	12	400.928
7/8	2.157	4-1/2	57.094	12-1/2	434.359
1	2.799	4-3/4	63.443	13	469.130
1-1/8	3.525	5	70.126	13-1/2	505.238
1-1/4	4.335	5-1/4	77.145	14	543.372
1-3/8	5.225	5-1/2	84.498	14-1/2	582.182
1-1/2	6.206	5-3/4	92.185	15	622.331
1-5/8	7.408	6	100.207	16	706.644
1-3/4	8.564	6-1/4	109.830	17	796.311
1-7/8	9.803	6-1/2	118.571	18	891.333
2	11.125	6-3/4	127.646	19	991.709
2-1/8	12.531	7	137.057	20	1097.440
2-1/4	14.021	7-1/4	149.891	22	1324.964
2-3/8	15.595	7-1/2	160.074	24	1573.907
2-1/2	17.252	7-3/4	170.592	26	1844.266
2-5/8	18.993	8	181.445	28	2136.044

**Notes:** For Powdered Metal add 3% for weight.

DC53 rounds under 6-1/2" are hot rolled and oversized to finish at their normal size. Rounds 6-1/2" and over are rough turned and oversized to finish at their normal size. DC-53 is ordered to metric sizes and the weight (lbs./ft.) may vary compared to the imperial measurements.

M2 rounds are available in on-size diameters and oversize diameters. M2 rounds are available in 3/8" to 6" diameters.

Alloys &  
Tool Steel

Alro Steel Metals Guide

# Tool Steel

## Thickness & Width Oversize Ranges

### De-Carb Free Flats and Squares

Size (inches)	Width - Based on Thickness (inches)	Thickness (inches)
Through 4" thick	+.035 / +.077 oversize	+.015 / +.035 oversize
Rough Milled 4" thru <5"	+.062 / +.124 oversize	+.062 / +.125 oversize
Rough Milled 5" and over	+.062 / +.124 oversize	+.125 / +.250 oversize

### De-Carb Rounds, Typical Machining Allowances

	Nominal Size (inches)	Oversize Tolerance (inches)
Rough Turned Tolerances:	1/2 to under 3	+0.007 to +0.062
	3 thru 6	+0.020 to +0.186
(All rounds 3" diameter and over are supplied with a Rough Turned tolerance)	Over 6 thru 7	+0.060 to +0.250
	Over 7 thru 18	+0.090 to +0.375
	Over 18	+0.118 to +0.375

### Machining and Decarburization Allowances

When ordering hot rolled bar stock, allowances must be made for machining in order to remove all decarburized surface. Decarburization is caused by heating for forging or rolling, and annealing. To obtain a uniform surface hardness and keep warpage to a minimum on finished tools, it is necessary to remove all the decarburization from all surfaces before hardening.

The minimum allowances for machining and the maximum decarburization limits for rounds, hexagons, octagons, and flats are given in the following tables.

Minimum Allowances Per Side for Machining Prior to Heat Treatment for Hot Rolled Rounds			
Ordered Size (inches)	Hot Rolled	Forged	Rounds Rough Turned
Up to 1/2, incl.	.016	—	—
Over 1/2 to 1, incl.	.031	—	—
Over 1 to 2, incl.	.048	.072	—
Over 2 to 3, incl.	.063	.094	.020
Over 3 to 4, incl.	.088	.120	.024
Over 4 to 5, incl.	.112	.145	.032
Over 5 to 6, incl.	.150	.170	.040
Over 6 to 8, incl.	.200	.200	.048
Over 8	—	.200	.072






# Tool Steel, Hot Rolled

## Machining and Decarburization Allowances

Maximum Decarburization Limits — 80% of allowances per side for machining

Minimum Allowances Per Side for Machining Prior to Heat Treatment for Hot-Rolled Square and Flat Bars



		Specified Width (inches)					
Specified Thickness (inches)		0 to 1/2 incl.	Over 1/2 to 1 incl.	Over 1 to 2 incl.	Over 2 to 3 incl.	Over 3 to 4 incl.	Over 4 to 5 incl.
0 to 1/2, incl.	A	.025	.025	.030	.035	.040	.045
	B	.025	.036	.044	.056	.068	.092
Over 1/2 to 1, incl.	A	---	.045	.045	.050	.055	.060
	B	---	.045	.052	.064	.080	.104
Over 1 to 2, incl.	A	---	---	.065	.065	.070	.070
	B	---	---	.065	.075	.084	.112
Over 2 to 3, incl.	A	---	---	---	.085	.085	.085
	B	---	---	---	.085	.102	.120
Over 3 to 4, incl.	A	---	---	---	---	.115	.115
	B	---	---	---	---	.115	.127
Over 4 to 5, incl.	A	---	---	---	---	---	.150
	B	---	---	---	---	---	.150
Over 5 to 6, incl.	A	---	---	---	---	---	---
	B	---	---	---	---	---	---
Over 6	A	---	---	---	---	---	---
	B	---	---	---	---	---	---

		Specified Width (inches)				
Specified Thickness (inches)		Over 5 to 6, incl.	Over 6 to 7, incl.	Over 7 to 8, incl.	Over 8 to 9, incl.	Over 9 to 10, incl.
0 to 1/2, incl.	A	.050	.055	.060	.060	.060
	B	.104	.120	.136	.144	.152
Over 1/2 to 1, incl.	A	.070	.070	.075	.075	.075
	B	.120	.136	.160	.160	.160
Over 1 to 2, incl.	A	.075	.075	.090	.095	.100
	B	.124	.144	.168	.180	.180
Over 2 to 3, incl.	A	.085	.090	.100	.100	.100
	B	.136	.160	.180	.190	.190
Over 3 to 4, incl.	A	.115	.115	.125	.125	.125
	B	.140	.180	.190	.190	.190
Over 4 to 5, incl.	A	.150	.150	.150	.150	.150
	B	.165	.180	.190	.190	.190
Over 5 to 6, incl.	A	.190	.190	.190	.190	.190
	B	.190	.190	.190	.190	.190
Over 6	A	---	.250	.250	.250	.250
	B	---	.250	.250	.250	.250

Alloys & Tool Steel


Alro Steel Metals Guide



# Tool Steel, Hot Rolled

## Machining and Decarburization Allowances

Minimum Allowances Per Side for  
Machining of Forged Squares and  
Flat Bars



Alloys &  
Tool Steel

		Specified Width (inches)					
Specified Thickness (inches)		0 to 1/2 incl.	Over 1/2 to 1 incl.	Over 1 to 2 incl.	Over 2 to 3 incl.	Over 3 to 4 incl.	Over 4 to 5 incl.
0 to 1/2, incl.	A	.030	.030	.035	.040	.045	.055
	B	.030	.048	.064	.080	.100	.120
Over 1/2 to 1, incl.	A	---	.060	.060	.065	.065	.075
	B	---	.060	.072	.084	.100	.120
Over 1 to 2, incl.	A	---	---	.090	.090	.090	.100
	B	---	---	.090	.100	.108	.124
Over 2 to 3, incl.	A	---	---	---	.120	.120	.125
	B	---	---	---	.120	.130	.140
Over 3 to 4, incl.	A	---	---	---	---	.150	.150
	B	---	---	---	---	.150	.150
Over 4 to 5, incl.	A	---	---	---	---	---	.180
	B	---	---	---	---	---	.180
Over 5 to 6, incl.	A	---	---	---	---	---	---
	B	---	---	---	---	---	---
Over 6	A	---	---	---	---	---	---
	B	---	---	---	---	---	---

		Specified Width (inches)				
Specified Thickness (inches)		Over 5 to 6, incl.	Over 6 to 7, incl.	Over 7 to 8, incl.	Over 8 to 9, incl.	Over 9 to 10, incl.
0 to 1/2, incl.	A	.065	.070	.075	---	---
	B	.144	.168	.200	---	---
Over 1/2 to 1, incl.	A	.080	.085	.090	.100	.110
	B	.144	.168	.200	.200	.200
Over 1 to 2, incl.	A	.110	.115	.125	.140	.150
	B	.148	.172	.200	.200	.200
Over 2 to 3, incl.	A	.130	.135	.150	.160	.175
	B	.148	.172	.200	.200	.200
Over 3 to 4, incl.	A	.160	.180	.190	.210	.225
	B	.160	.180	.190	.210	.225
Over 4 to 5, incl.	A	.180	.190	.210	.225	.250
	B	.180	.190	.210	.225	.250
Over 5 to 6, incl.	A	.210	.225	.225	.250	.250
	B	.210	.225	.225	.250	.250
Over 6	A	---	.250	.250	.250	.250
	B	---	.250	.250	.250	.250